





2

**HIGH TEMPERATURE WIRES AND CABLES
FOR THE GENERAL MARKET**
SECTION II: FLUOROPOLYMERS AND THERMOPLASTICS

omerin
LES CABLES DE L'EXTREME




- The world's leading manufacturer of silicone-insulated wires and cables
- Europe's leading manufacturer of glass-yarn braids
- France's leading manufacturer of fire safety cables

The Omerin group has been producing electrical cables for extreme conditions since 1959

At Omerin, we use our know-how and technology to develop increasingly high-performance products.

Our expertise is recognized in over 120 countries.



Omerin offers a wide range of high-performance products covering a large number of applications in very diverse industries, including the electrothermal construction, electromechanical, chemical, nuclear energy, railway, automotive, naval, aerospace, heavy industry, power plant and other sectors.

Our product range is further extended by varnished, impregnated and treated braided insulating sleeveings, door seals for ovens, fireproof sleeveings, thermocouple, extension and compensation cables as well as industrial braids.



Men and women at your service

The technical expertise of our teams is at your disposal, providing responses and solutions to all your requirements.

Our Methods, Quality and Research and Development Departments work permanently together with the aim of constantly improving our products and processes.

All our staff subscribe to this approach with their involvement and constant self-checking at all stages of production.

List of all the available catalogues:

HIGH TEMPERATURE WIRES AND CABLES FOR THE GENERAL MARKET SECTION I: CROSS LINKED ELASTOMERS 1

HIGH TEMPERATURE WIRES AND CABLES FOR THE GENERAL MARKET SECTION II: FLUOROPOLYMERS AND THERMOPLASTICS 2

HIGH TEMPERATURE WIRES AND CABLES FOR THE GENERAL MARKET SECTION III: COMPOSITE INSULATIONS 3

FIRE RESISTANT SAFETY CABLES 4

CABLE SOLUTIONS FOR ROLLING STOCK 5

CABLES FOR POWER STATIONS AND HIGH-RISK SITES 6

MARINE CABLES 7

PYROMETRY CABLES 8

BRAIDED INSULATING SLEEVINGS 9

HIGH TEMPERATURE MEDIUM VOLTAGE POWER CABLES 10

CABLE SOLUTIONS FOR AUTOMOTIVE AND E-MOBILITY 11

PACKAGING AND TECHNICAL DATA

Ultimately, this catalogue is the result of the passionate endeavours of an entire team, who have displayed great talent in writing it for you.

It is designed to be a simple and concise working tool for you, serving as a reference document that is able to meet the majority of your needs.

This catalogue, as well as ten others from our collection are available on line with real time updates and much more information at



www.omerin.com

All the trademarks listed below are registered trademarks of the **OMERIN Group**.

BIO-HABITAT®	Wires and cables for a home without electromagnetic interference
CERAFIL®	Miniature ceramic insulated wires for very high temperatures
COAXRAIL®	Coaxial cables for railway industry
COAXTHERM®	High temperature coaxial cables
COUPLIX®	Pyrometry cables (thermocouples, extension, compensation cables)
DATARAIL®	Data cables for the railway industry
ELECTROAIR®	Aerospace & Defence wires and cables
ENERSYL®	Electrical cables for power station and high risk sites
FLEXBAT®	Extra flexible battery cables
LUMIPLAST®	Wires and cables for lighting systems
METALTRESSE®	High performance metallic braids
MINOROC®	Very high tensile strength synthetic cables
MULTIMAX®	Power, control and instrumentation cables for the marine industry
MULTI-VX®	Hybrid data and power cables
ODIOSIS®	Sound, amplification and loudspeaker cables
OILPLAST®	Cables for industrial environments and intrinsically safe system
OMBILIFLEX®	High performance special multi-function cables
PLASTHERM®	Special thermoplastic insulated wires and cables
POWER CONNECT®	High performance power cords
PROFIPLAST®	Thermoplastic insulated wires and cables
PYRISOL®	Fire resistant power cables for safety circuits
PYRITEL®	Fire resistant communication cables for safety circuits
SILIBOX®	Wire and cables cardboard box packaging system
SILICABLE®	Special high temperature wires and cables
SILICOUL®	Low and medium voltage class H (180°C) power cables
SILIFLAM®	Very high safety cables for extreme temperatures
SILIFLON®	Fluoropolymer insulated high temperature wires and cables
SILIGAIN®	Braided insulating sleeveings
SILIRAD®	Electron beam crosslinked cables
SILITUBE®	Braided or extruded tubes
SOLARPLAST®	Power cables for photovoltaic solar panels
SONDIX®	Platinum resistance temperature sensors connection cables
SPIRFLEX®	High performance spiral cables
TEXALARM®	Cables for safety systems and fire alarms
TS CABLES®	Coaxial and data cables
TS COM 900®	Telephonic cables for very speed reception
TS LAN®	Copper LAN cables
TWINLINK®	High temperature controlled impedance twisted pair cables
TWINPLAST®	Extra flexible cables for battery chargers or jump starters
VARPREN®	Wires and cables with special cross-linked Varpren® insulation
VEROX®	Fiberglass braided seals
VIDEOCOAX®	Analog and digital video cables



Thermal classification of insulations



Contents

**FLUOROPOLYMER INSULATED
WIRES AND CABLES**

FT 2101 to 2131

Pages 6 to 45

**THERMOPLASTIC INSULATED
WIRES AND CABLES**

FT 2201 to 2218

Pages 48 to 69

Product list

FLUOROPOLYMER INSULATED WIRES AND CABLES


















FTNo.	PRODUCT REFERENCE	PAGE
2101	SILIFLON ETFE and EETFE.....	6
2102	SILIFLON KU 01 and KU 02.....	7
2103	SILIFLON 7YA	8
2104	SILIFLON 7Y.....	9
2105	SILIFLON LI7Y	10
2106	SILIFLON FEP and EFEP.....	12
2107	SILIFLON 6YS.....	13
2108	SILIFLON 6Y6YS and E6Y6YS.....	14
2109	SILIFLON PFA and EPFA	15
2110	SILIFLON 51YS.....	16
2111	SILIFLON RETFE, RFEP and RPFA.....	17
2112	SILIFLON 105 °C - Fluoropolymer insulation.....	18
2113	SILIFLON Style 10935.....	19
2132	SILIFLON Style 11881	20
2114	SILIFLON 150 °C - Fluoropolymer insulation.....	22
2115	SILIFLON 200 °C - Fluoropolymer insulation.....	24

FTNo.	PRODUCT REFERENCE	PAGE
2116	SILIFLON 250 °C - Fluoropolymer insulation.....	26
2117	SILIFLON KZ 04.....	28
2118	SILIFLON KZ 05.....	29
2119	SILIFLON KZ 06.....	30
2120	SILIFLON KZ 07.....	31
2121	SILIFLON KZ 08.....	32
2122	SILIFLON KZ 09.....	33
2123	SILIFLON CN5YS and A5YS	34
2124	SILIFLON Style 10506	35
2125	SILIFLON HT - Ignition wires	36
2126	SILIFLON HT - Ignition wires	37
2127	SILIFLON M6-E6.....	38
2128	SILIFLON M6BE-E6	40
2129	SILIFLON KU 03, KU 04, KU 05, KU 06	42
2130	SILIFLON 150 °C - Fluoropolymer insulation and sheathing	43
2131	SILIFLON 200 °C - Fluoropolymer insulation and sheathing	44

THERMOPLASTIC INSULATED WIRES AND CABLES

FTNo.	PRODUCT REFERENCE	PAGE
2201	PLASTHERM Y2 and EY2	48
2202	PLASTHERM 80 °C - PVC insulation	50
2203	PLASTHERM 105 °C - PVC insulation	52
2204	PLASTHERM Style 1015-HAR	54
2205	PLASTHERM Style 20199, 2-conductor flat cable	55
2206	PLASTHERM MY2-Y2 and MY2-EY2	56
2207	PLASTHERM 80 °C - PVC insulation and sheathing...58	
2208	PLASTHERM 90 °C - PVC insulation and sheathing...59	
2209	PLASTHERM 105 °C - PVC insulation and sheathing.60	
2210	PLASTHERM 90 °C - Polyolefin insulation	61
2211	PLASTHERM PHF2 - Halogen-free insulation	62
2212	PLASTHERM PHF2E IRD - Halogen-free insulation63	
2213	PLASTHERM PHFLEX - Resistant to alternate bending .64	
2214	PLASTHERM style 21209 - Polyurethane sheathing...65	
2215	PLASTHERM MYBE-EY-CSI - Intrinsic safety	66
2216	PLASTHERM HP-U - 2-conductor flat cable.....67	
2217	PLASTHERM HP-M - 2-conductor flat cable.....68	
2218	PLASTHERM HP-M-HT - 2-conductor flat cable	69

FLUOROPOLYMER INSULATED WIRES AND CABLES

FT No.	PRODUCT REFERENCE	APPROVAL	PAGE
2101	SILIFLON ETFE and EETFE		6
2102	SILIFLON KU 01 and KU 02		7
2103	SILIFLON 7YA		8
2104	SILIFLON 7Y		9
2105	SILIFLON LI7Y		10
2106	SILIFLON FEP and EFEP		12
2107	SILIFLON 6YS		13
2108	SILIFLON 6Y6YS and E6Y6YS		14
2109	SILIFLON PFA and EPFA		15
2110	SILIFLON 51YS		16
2111	SILIFLON RETFE, RFEP and RPFA		17
2112	SILIFLON 105 °C - Fluoropolymer insulation		18
2113	SILIFLON Style 10935		19
2132	SILIFLON Style 11881		20
2114	SILIFLON 150 °C - Fluoropolymer insulation		22
2115	SILIFLON 200 °C - Fluoropolymer insulation		24
2116	SILIFLON 250 °C - Fluoropolymer insulation		26
2117	SILIFLON KZ 04		28
2118	SILIFLON KZ 05		29
2119	SILIFLON KZ 06		30
2120	SILIFLON KZ 07		31
2121	SILIFLON KZ 08		32
2122	SILIFLON KZ 09		33
2123	SILIFLON CN5YS and A5YS		34
2124	SILIFLON Style 10506		35
2125	SILIFLON HT - Ignition wires		36
2126	SILIFLON HT - Ignition wires		37
2127	SILIFLON M6-E6		38
2128	SILIFLON M6BE-E6		40
2129	SILIFLON KU 03, KU 04, KU 05, KU 06		42
2130	SILIFLON 150 °C - Fluoropolymer insulation and sheathing		43
2131	SILIFLON 200 °C - Fluoropolymer insulation and sheathing		44

SILIFLON® ETFE and EETFE

-90 °C to +155 °C

Approvals - standards

- Series inspired by standards
NF C 93-524

Applications

- Cabling for rotating machines (class F).
- Cabling in household electrical appliances, electronics.
- Cabling in hot or cold environments (cryogenics).
- Cabling in aggressive environments (humidity, chemicals, etc.).
- Cabling requiring compact size and excellent mechanical strength.

Options

- Nickel-plated copper core: ref. CNETFE.
- Silver-plated copper core: ref. AETFE.
- Pure nickel core: ref. NETFE.
- Outer electrical shielding:
 - Tin-plated copper braid: ref. ETFEBE or EETFEBE.
 - Other nominal metric or American cross-sections: contact us.
 - Other nominal stranding: contact us.
- Other options and/or combinations of the options outlined above: contact us.



- 1 • Bare (ref. ETFE) or tin-plated (ref. EETFE) copper core.
- 2 • Insulation: Fluorinated polymer ETFE.

Characteristics

General

- Continuous operating temperatures: -90 °C to +155 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 450/750 V.
- Test voltage: 2500 V.

Standard products

- All colours including translucent.

ETFE and EETFE

CONDUCTING CORE			INSULATED WIRE OR CABLE		
Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km) (bare copper core)	Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.05	7 x 0.10	373	0.17	0.65	0.9
0.09	7 x 0.13	214	0.17	0.7	1.3
0.12*	7 x 0.15	161	0.17	0.8	1.7
0.14**	7 x 0.16	141	0.17	0.8	1.8
0.15	19 x 0.10	136	0.20	0.9	2.1
0.22	7 x 0.20	89.9	0.20	1.0	2.7
0.25	19 x 0.13	80.0	0.20	1.05	3.2
0.34	7 x 0.25	57.5	0.20	1.15	4.0
0.38**	19 x 0.16	54.1	0.20	1.15	4.4
0.5	7 x 0.30	39.6	0.20	1.3	5.6
0.5	16 x 0.20	39.0	0.20	1.3	5.9
0.6	19 x 0.20	32.8	0.20	1.4	6.4
0.75	24 x 0.20	26.0	0.20	1.45	8.5
0.88	7 x 0.40	22.2	0.20	1.5	9.0
0.93	19 x 0.25	21.0	0.20	1.7	10.0
1	32 x 0.20	19.5	0.20	1.7	11.4
1.34	19 x 0.30	14.6	0.20	1.9	13.9
1.5	30 x 0.25	13.3	0.20	1.95	15.6
2.5	50 x 0.25	7.98	0.20	2.5	25.6
4	56 x 0.30	4.95	0.25	3.1	38.9
6	84 x 0.30	3.30	0.35	3.9	55.6
10	80 x 0.40	1.91	0.40	5.2	101
16	126 x 0.40	1.21	0.40	6.5	147
25	196 x 0.40	0.780	0.60	8.2	242
35	276 x 0.40	0.554	0.60	9.2	320
50	396 x 0.40	0.386	0.70	11.2	465

** Nominal cross-section not available with the ref. EETFE.

** Nominal cross-sections not available with the ref. ETFE.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

omerin
LES CABLES DE L'EXTREME

SILIFLON® KU 01 and KU 02

-55 °C to +150 °C

Approvals - standards

- Inspired from NF C 93-524 standard.

Applications

- Wires used in aeronautical and electronic applications and all instrumentation uses requiring excellent resistance to high temperatures and to chemical influences.

Options

- Compliance with American standards SAE AS 22756/16 and SAE AS 22759/18: contact us.
- Other colours: contact us.

Characteristics

General


- Continuous operating temperatures: -55 °C to +150 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical (as per UTE C 93-524)

- Rated voltage: 600 Vac – 850 Vdc.
- Test voltage: KU 01: 3400 Vac.
KU 02: 1500 Vac.

Standard products

- Standard insulation colour: white.
- Standard outer sheath colour: white.



- 1 • Concentric tin-plated copper core.
- 2 • Insulation: Fluorinated polymer ETFE.
- 3 • Electrical shielding: Tin-plated copper braid.
- 4 • Outer sheath: Fluorinated polymer ETFE.

KU 01 and KU 02

CONCENTRIC CORE

Nominal cross-section AWG	Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
30	0.05	7 x 0.10	365.4
28	0.09	7 x 0.13	208.0
26	0.15	19 x 0.10	128.7
24	0.25	19 x 0.13	76.6
22	0.38	19 x 0.16	50.3
20	0.60	19 x 0.20	32.1
18	0.93	19 x 0.25	20.6
16	1.34	19 x 0.30	14.3
14	1.82	37 x 0.25	10.6
12	3.00	37 x 0.32	6.5

INSULATED WIRE

KU 01		KU 02	
Nominal diameter (mm)	Approximate linear weight (kg/km)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.63	0.9	1.33	4.7
0.69	1.3	1.39	5.0
0.81	1.9	1.51	5.8
0.91	2.8	1.71	7.2
1.10	4.2	1.96	10.1
1.52	6.9	2.38	13.4
1.80	10.5	2.76	19.3
2.00	14.4	2.96	23.5
2.36	19.5	3.32	30.8
2.89	36.1	3.85	48.1

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® 7YA

VDE approval

-90 °C to +135 °C



Approvals - standards

- 7YA: VDE approval as per standards DIN VDE 0250 Part 1 and DIN VDE 0250 Part 106 - Licence no. 88272.

Applications

- Cabling in household electrical appliances, electronics.
- Cabling in hot or cold environments (cryogenics).
- Cabling in aggressive environments (humidity, chemicals, etc.).
- Cabling requiring compact size and excellent mechanical strength.

Characteristics General

- Continuous operating temperatures:
 - > Bare copper core: -90 °C to +130 °C.
 - > Tin-plated, nickel-plated or silver-plated copper core: -90 °C to +135 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

7YA

- Rated voltage: 450/750 V
- Test voltage: 2500 V

Standard products

- All colours including translucent.

Options

- Flexible tin-plated copper core – ref. E7YA and E7YS: contact us.
- Flexible nickel-plated copper core – ref. CN7YA and CN7YS: contact us.
- Flexible silver-plated copper core – ref. A7YA and A7YS: contact us.
- Solid bare copper core – ref. R7YA and R7YS: see details of the option below.
- Solid tin-plated copper core – ref. RE7YA and RE7YS: contact us.

7YA

Flexible core • class 5 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.25*	19 x 0.13 or 7 x 0.22	80.7
0.5	16 x 0.20	39.0
0.75	24 x 0.20	26.0
1	32 x 0.20	19.5
1.5	30 x 0.25	13.3
2.5	50 x 0.25	7.98
4	56 x 0.30	4.95
6	84 x 0.30	3.30

INSULATED WIRE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.40	1.45	4.6
0.40	1.7	7.8
0.40	1.85	9.9
0.40	2.0	12.6
0.50	2.4	18.9
0.60	3.1	31.0
0.60	3.8	43.6
0.60	4.3	60.1

Option • R7YA

Solid core • class 1 as per IEC 60228

Nominal cross-section (mm ²)	Nominal diameter (mm)	Maximum linear resistance at 20 °C (Ω/km)	Approximate linear weight (kg/km)
0.25*	1 x 0.56	73.4	4.2
0.5	1 x 0.80	36.0	7.1
0.75	1 x 0.98	24.5	9.8
1	1 x 1.13	18.1	12.4
1.5	1 x 1.36	12.1	18.3
2.5	1 x 1.77	7.41	30.0
4	1 x 2.24	4.61	44.7
6	1 x 2.74	3.08	63.9

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* Nominal cross-section not included in IEC 60228.

(1) Standardised name: N7YAF VDE.

(2) Standardised name: N7YA VDE.

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® 7Y

VDE approval
-90 °C to +135 °C



- 1 • Solid bare or tin-plated copper core.
- 2 • Insulation: Fluorinated polymer ETFE.

Approvals - standards

- VDE approval as per standard DIN VDE 0881 - licence no. 088244.

Applications

- Cabling in electronics and household appliances.
 - Cabling in hot and aggressive environments (humidity, chemicals, etc.).

Options

- Solid silver-plated copper core: contact us.
 - Twisted pair or triple or quad with no outer sheath - Standardised reference: 7Y n x Cross-section/Østranding (n being the number of twisted conductors).

Characteristics General

- Continuous operating temperatures: -90 °C to +135 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage:
 - > Nominal thickness of insulation (0.15 mm): 375 V.
 - > Nominal thickness of insulation (0.25 mm): 900 V.
- Test voltage:
 - > Nominal thickness of insulation (0.15 mm): 1500 V.
 - > Nominal thickness of insulation (0.25 mm): 2500 V.

Standard products

- All colours including translucent.

7Y

SOLID CORE				INSULATED WIRE		
Standardised reference	Nominal cross-section	Nominal stranding	Maximum linear resistance at 20 °C	Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
	(mm ²)		(Ω/km) (bare copper core)			
7Y 1 x 0.25/0.55	0.05	1 x 0.25	384	0.15	0.55	0.8
7Y 1 x 0.32/0.6*	0.08	1 x 0.32	230	0.15	0.62	1.1
7Y 1 x 0.4 /0.7	0.125	1 x 0.40	146	0.15	0.7	1.6
7Y 1 x 0.5 /0.8	0.20	1 x 0.50	93.1	0.15	0.8	2.3
7Y 1 x 0.63/0.95*	0.31	1 x 0.63	58.7	0.15	0.93	3.4
7Y 1 x 0.8 /1.1	0.50	1 x 0.80	36.0	0.15	1.1	5.3
7Y 1 x 0.25/0.75	0.05	1 x 0.25	384	0.25	0.75	1.1
7Y 1 x 0.32/0.8*	0.08	1 x 0.32	230	0.25	0.82	1.5
7Y 1 x 0.4 /0.9	0.125	1 x 0.40	146	0.25	0.9	2.0
7Y 1 x 0.5 /1.0	0.20	1 x 0.50	93.1	0.25	1.0	2.8
7Y 1 x 0.63/1.2*	0.31	1 x 0.63	58.7	0.25	1.13	4.0
7Y 1 x 0.8 /1.3	0.50	1 x 0.80	36.0	0.25	1.3	5.9
7Y 1 x 1.0 /1.5*	0.785	1 x 1.00	23.1	0.25	1.5	8.7
7Y 1 x 1.3 /1.8*	1.33	1 x 1.30	13.6	0.25	1.8	14.0
7Y 1 x 1.6 /2.1*	2.01	1 x 1.60	9.01	0.25	2.1	20.6
7Y 1 x 2.1 /2.6*	3.46	1 x 2.10	5.23	0.25	2.6	34.3

* Contact us.

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® Li7Y
VDE approval**-90 °C to +135 °C**

- 1 • Concentric bare, tin-plated or silver-plated copper core.
- 2 • Insulation: Fluorinated polymer ETFE.

Approvals - standards

- VDE approval as per standard
DIN VDE 0881 - licence no. 085392.

Applications

- Cabling in electronics and household appliances.
 - Cabling in hot and aggressive environments (humidity, chemicals, etc.).

Options

- Twisted pair or triple or quad with no outer sheath -
Standardised reference:
Li7Y n x Cross-section/Østranding
(n being the number of twisted conductors).

Characteristics**General**

- Continuous operating temperatures: -90 °C to +135 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage:
 - > Nominal thickness of insulation (0.15 mm): 375 V.
 - > Nominal thickness of insulation (0.25 mm): 900 V.
 - > Nominal thickness of insulation (0.40 mm): 1500 V.
 - > Nominal thickness of "ECO" insulation: 900 V.
- Test voltage:
 - > Nominal thickness of insulation (0.15 mm): 1500 V.
 - > Nominal thickness of insulation (0.25 mm): 2500 V.
 - > Nominal thickness of insulation (0.40 mm): 3000 V.
 - > Nominal thickness of "ECO" insulation: 2500 V.

Standard products

- All colours including translucent.

For this product, please contact:

OMERIN division principale

Zone Industrielle - F 63600 Ambert

Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10

omerin@omerin.com

omerin
LES CABLES DE L'EXTREMEwww.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.

For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

CONCENTRIC CORE

Standardised reference	Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km) (bare copper core)
Standardised series			
Li7Y 1 x 0.055/0.6	0.055	7 x 0.10	349
Li7Y 1 x 0.079/0.7	0.079	7 x 0.12	236
Li7Y 1 x 0.12 /0.8	0.12	7 x 0.15	151
Li7Y 1 x 0.22 /0.9	0.22	7 x 0.20	84.8
Li7Y 1 x 0.34 /1.1	0.34	7 x 0.25	54.3
Li7Y 1 x 0.56 /1.3	0.56	19 x 0.20**	32.5
Li7Y 1 x 0.055/0.8	0.055	7 x 0.10	349
Li7Y 1 x 0.079/0.9	0.079	7 x 0.12	236
Li7Y 1 x 0.12 /1.0	0.12	7 x 0.15	151
Li7Y 1 x 0.22 /1.1	0.22	7 x 0.20	84.8
Li7Y 1 x 0.34 /1.3	0.34	7 x 0.25	54.3
Li7Y 1 x 0.56 /1.5	0.56	19 x 0.20**	32.5
Li7Y 1 x 0.93 /1.8	0.93	19 x 0.25	20.0
Li7Y 1 x 1.3 /2.0	1.3	19 x 0.29	14.9
Li7Y 1 x 1.9 /2.3	1.9	19 x 0.36	9.46
Li7Y 1 x 3.2 /2.8	3.2	19 x 0.46	5.79
Li7Y 1 x 0.12 /1.3	0.12	7 x 0.15	151
Li7Y 1 x 0.22 /1.4	0.22	7 x 0.20	84.8
Li7Y 1 x 0.34 /1.6	0.34	7 x 0.25	54.3
Li7Y 1 x 0.56 /1.8	0.56	19 x 0.20**	32.5
Li7Y 1 x 0.93 /2.1	0.93	19 x 0.25	20.0
Li7Y 1 x 1.3 /2.3	1.3	19 x 0.29	14.9
Li7Y 1 x 1.9 /2.6	1.9	19 x 0.36	9.46
Li7Y 1 x 3.2 /3.1	3.2	19 x 0.46	5.79
Li7Y 1 x 4.6 /3.6	4.6	37 x 0.40	3.93
Li7Y 1 x 8.8 /5.2	8.8	133 x 0.29*	2.12
Li7Y 1 x 13.5 /6.2	13.5	133 x 0.36*	1.35
Economical series			
Li7Y 1 x 0.15 /0.8	0.15	19 x 0.10	135
Li7Y 1 x 0.22 /0.9	0.22	19 x 0.12	86.0
Li7Y 1 x 0.36 /1.1	0.36	19 x 0.15	53.2
Li7Y 1 x 0.59 /1.3	0.59	19 x 0.20	32.4
Li7Y 1 x 0.93 /1.55	0.93	19 x 0.25	20.4
Li7Y 1 x 1.3 /1.8	1.3	19 x 0.29	15.8
Li7Y 1 x 1.9 /2.15	1.9	19 x 0.36	10.0
Li7Y 1 x 2.8 /2.7	2.8	37 x 0.31	6.63
Li7Y 1 x 4.6 /3.4	4.6	37 x 0.40	4.13

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.15	0.6	0.9
0.15	0.65	1.1
0.15	0.75	1.6
0.15	0.9	2.6
0.15	1.05	3.8
0.15	1.25	5.9
0.25	0.8	1.2
0.25	0.85	1.5
0.25	0.95	2.0
0.25	1.1	3.1
0.25	1.25	4.4
0.25	1.45	6.6
0.25	1.75	10.4
0.25	1.95	13.6
0.25	2.3	20.1
0.25	2.8	31.8
0.40	1.25	2.9
0.40	1.4	4.1
0.40	1.55	5.5
0.40	1.75	7.9
0.40	2.05	11.9
0.40	2.25	15.2
0.40	2.6	22.1
0.40	3.1	34.2
0.40	3.6	48.7
0.60	5.2	93.8
0.60	6.25	140
0.16	0.8	1.9
0.16	0.9	2.5
0.16	1.1	3.9
0.17	1.3	6.3
0.17	1.55	9.5
0.21	1.8	12.8
0.23	2.15	19.3
0.26	2.7	28.6
0.32	3.4	46.8

* Non-concentric cores.

** Nominal stranding not defined in standard DIN VDE 0881.

For this product, please contact:

OMERIN division principale 
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com

www.omerin.com

omerin
 LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
 For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 ® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® FEP and EFEP**-90 °C to +205 °C****Approvals - standards**

- Series inspired by standards NF C 93-524 and DIN VDE 0250 Part 106.

Applications

- Cabling for rotating machines.
- Cabling in household electrical appliances, electronics.
- Cabling in hot or cold environments (cryogenics).
- Cabling in aggressive environments (humidity, chemicals, etc.).
- Cabling requiring compact size and excellent mechanical strength.

Options

- Nickel-plated copper core: ref. CNFEP.
- Silver-plated copper core: ref. AFEP.
 - Pure nickel core: ref. NFEP.
 - Outer electrical shielding:
- Tin-plated copper braid: ref. FEPBE or EFEPBE.
- Other nominal metric or American cross-sections: contact us.
- Other nominal stranding: contact us.
- Other options and/or combinations of the options outlined above: contact us.

Characteristics**General**

- Continuous operating temperatures: -90 °C to +205 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 450/750 V.
- Test voltage: 2500 V.

Standard products

- All colours including translucent.



- 1 • Bare (ref. FEP) or tin-plated (ref. EFEP) copper core.
- 2 • Insulation: Fluorinated polymer FEP.

FEP and EFEP**CONDUCTING CORE**

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km) (bare copper core)
0.05	7 x 0.10	373
0.09	7 x 0.13	214
0.12*	7 x 0.15	161
0.14**	7 x 0.16	141
0.15	19 x 0.10	136
0.22	7 x 0.20	89.9
0.25	19 x 0.13	80.0
0.34	7 x 0.25	57.5
0.38**	19 x 0.16	54.1
0.5	7 x 0.30	39.6
0.5	16 x 0.20	39.0
0.6	19 x 0.20	32.8
0.75	24 x 0.20	26.0
0.88	7 x 0.40	22.2
0.93	19 x 0.25	21.0
1	32 x 0.20	19.5
1.34	19 x 0.30	14.6
1.5	30 x 0.25	13.3
2.5	50 x 0.25	7.98
4	56 x 0.30	4.95
6	84 x 0.30	3.30
10	80 x 0.40	1.91
16	126 x 0.40	1.21
25	196 x 0.40	0.780
35	276 x 0.40	0.554
50	396 x 0.40	0.386

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.17	0.65	1.1
0.17	0.7	1.4
0.17	0.8	1.9
0.17	0.8	2.0
0.20	0.9	2.3
0.20	1.0	3.0
0.20	1.05	3.4
0.20	1.15	4.3
0.20	1.15	4.6
0.20	1.3	5.9
0.20	1.3	6.2
0.20	1.4	6.7
0.20	1.45	8.8
0.20	1.5	9.3
0.20	1.7	10.5
0.20	1.7	11.9
0.20	1.9	14.3
0.20	1.95	16.3
0.20	2.5	26.6
0.25	3.1	40.4
0.35	3.9	57.7
0.40	5.2	104
0.40	6.2	150
0.60	8.2	248
0.60	9.2	328
0.70	11.2	478

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* Nominal cross-section not available with the ref. EFEP.

** Nominal cross-sections not available with the ref. FEP.

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® 6YS

VDE approval
-90 °C to +180 °C

Approvals - standards

- 6YS: VDE approval as per standard DIN VDE 0250 Part 106 - Licence no. 107583.



Applications

- Cabling in household electrical appliances, electronics.
 - Cabling in hot or cold environments (cryogenics).
 - Cabling in aggressive environments (humidity, chemicals, etc.).
- Cabling requiring compact size and excellent mechanical strength.

Characteristics

General

- Continuous operating temperatures:
 - > Bare copper core: -90 °C to +130 °C.
 - > Tin-plated, nickel-plated or silver-plated copper core: -90 °C to +180 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical 6YS

- Rated voltage: 300/500 V.
- Test voltage: 2000 V.

Standard products

- All colours including translucent.

Options

- Flexible tin-plated copper core – ref. E6YA and E6YS: contact us.
- Flexible nickel-plated copper core – ref. CN6YA and CN6YS: contact us.
- Flexible silver-plated copper core – ref. A6YA and A6YS: contact us.
- Solid bare copper core – ref. R6YA and R6YS: see details of the option below.
- Solid tin-plated copper core – ref. RE6YA and RE6YS: contact us.

6YS

Flexible core • class 5 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.25*	19 x 0.13 or 7 x 0.22	80.7
0.5	16 x 0.20	39.0
0.6*	19 x 0.20	32.8
0.75	24 x 0.20	26.0
1	32 x 0.20	19.5
1.5	30 x 0.25	13.3
2.5	50 x 0.25	7.98
4	56 x 0.30	4.95
6	84 x 0.30	3.30

INSULATED WIRE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.30	1.25	4.2
0.30	1.5	6.5
0.30	1.5	7.4
0.30	1.65	8.7
0.30	1.8	10.9
0.30	2.0	14.9
0.35	2.6	25.0
0.40	3.4	41.9
0.40	3.9	60.1

Option • R6YS

Solid core • class 1 as per IEC 60228

0.25*	1 x 0.56	73.4	0.30	1.15	3.9
0.5	1 x 0.80	36.0	0.30	1.4	6.8
0.75	1 x 0.98	24.5	0.30	1.6	9.5
1	1 x 1.13	18.1	0.30	1.75	12.0
1.5	1 x 1.36	12.1	0.30	2.0	16.7
2.5	1 x 1.77	7.41	0.35	2.5	27.4
4	1 x 2.24	4.61	0.40	3.05	42.7
6	1 x 2.74	3.08	0.40	3.55	61.7

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* Nominal cross-sections not described in IEC 60228.

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON®

6Y6YS and E6Y6YS

Double insulating layer
VDE approval
-90 °C to +180 °C



Approvals - standards

- VDE approval as per standard DIN VDE 0250 Part 106 - Licence no. 40001865.

Applications

- Cabling for class 2 light fittings, household electrical appliances, electronics, etc.
- Cabling in hot or cold environments (cryogenics).
 - Cabling in aggressive environments (humidity, chemicals, etc.).
 - Cabling in the medical field.
 - Cabling requiring compact size and excellent mechanical strength.

Options

- Nickel-plated copper core – ref. CN6Y6YS: contact us.
- Silver-plated copper core – ref. A6Y6YS: contact us.
- Solid bare (ref. R6Y6YS) or tin-plated (ref. RE6Y6YS) copper core: See details of the option below.

Characteristics

General

- Continuous operating temperatures:
 - > Bare copper core: -90 °C to +130 °C.
 - > Tin-plated, nickel-plated or silver-plated copper core: -90 °C to +180 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 300/500 V.
- Test voltage: 2000 V.

Standard products

- All solid colours.



- Multistrand bare (ref. 6Y6YS) or tin-plated (ref. E6Y6YS) copper core.
- Insulation: Fluorinated polymer FEP.

6Y6YS and E6Y6YS

MULTISTRAND CORE

AWG	Nominal cross-section	Nominal stranding	Maximum linear resistance at 20 °C (Ω /km) (tin-plated copper core)
	(mm ²)		
24	0.25	19 x 0.13	82.9
22	0.34	7 x 0.25	60.6
-	0.38	19 x 0.16	55.7
-	0.5	16 x 0.20	40.1
-	0.5	7 x 0.30	36.7
20	0.6	19 x 0.20	33.7
18	0.75	24 x 0.20	26.7
-	0.93	19 x 0.25	21.6
-	1	32 x 0.20	20.0
16	1.34	19 x 0.30	15.0
-	1.5	30 x 0.25	13.7

Option • R6Y6YS and RE6Y6YS

SOLID CORE

	Nominal cross-section	Nominal stranding	Maximum linear resistance at 20 °C (Ω /km)
-	0.25	1 x 0.56	74.8
-	0.5	1 x 0.80	36.7
-	0.75	1 x 0.98	24.8
-	1	1 x 1.13	18.2
-	1.5	1 x 1.38	12.2

INSULATED WIRE

Nominal thickness of insulation	Nominal diameter	Approximate linear weight
(mm)	(mm)	(kg/km)
0.60	1.85	7.3
0.60	1.95	8.5
0.60	2.0	9.1
0.60	2.1	10.5
0.60	2.1	10.5
0.60	2.15	11.4
0.60	2.25	13.8
0.60	2.4	15.4
0.60	2.45	17.2
0.60	2.6	20.2
0.60	2.65	21.7

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® PFA and EPFA

-90 °C to +260 °C



- 1 • Bare (ref. PFA) or tin-plated (ref. EPFA) copper core.
- 2 • Insulation: Fluorinated polymer PFA.

Approvals - standards

- Series inspired by standards NF C 93-524 and DIN VDE 0250 Part 106.

Applications

- Cabling for rotating machines.
- Cabling in household electrical appliances, electronics.
 - Cabling in hot or cold environments (cryogenics).
 - Cabling in aggressive environments (humidity, chemicals, etc.).
- Cabling requiring compact size and excellent mechanical strength.

Options

- Nickel-plated copper core: ref. CNPFA.
- Silver-plated copper core: ref. APFA.
 - Pure nickel core: ref. NPFA.
 - Outer electrical shielding:
 - > Tin-plated copper braid: ref. PFABE or EPFABE.
- Other nominal metric or American cross-sections: contact us.
- Other nominal stranding: contact us.
- Other options and/or combinations of the options outlined above: contact us.

Characteristics

General

- Continuous operating temperatures: -90 °C to +260 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 450/750 V.
- Test voltage: 2500 V.

Standard products

- All colours including translucent.

PFA and EPFA

CONDUCTING CORE			INSULATED WIRE OR CABLE		
Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km) (bare copper core)	Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.05	7 x 0.10	373	0.17	0.65	1.1
0.09	7 x 0.13	214	0.17	0.7	1.4
0.12*	7 x 0.15	161	0.17	0.8	1.9
0.14**	7 x 0.16	141	0.17	0.8	2.0
0.15	19 x 0.10	136	0.20	0.9	2.3
0.22	7 x 0.20	89.9	0.20	1.0	3.0
0.25	19 x 0.13	80.0	0.20	1.05	3.4
0.34	7 x 0.25	57.5	0.20	1.15	4.3
0.38**	19 x 0.16	54.1	0.20	1.15	4.6
0.5	7 x 0.30	39.6	0.20	1.3	5.9
0.5	16 x 0.20	39.0	0.20	1.3	6.2
0.6	19 x 0.20	32.8	0.20	1.4	6.7
0.75	24 x 0.20	26.0	0.20	1.45	8.8
0.88	7 x 0.40	22.2	0.20	1.5	9.3
0.93	19 x 0.25	21.0	0.20	1.7	10.5
1	32 x 0.20	19.5	0.20	1.7	11.9
1.34	19 x 0.30	14.6	0.20	1.9	14.3
1.5	30 x 0.25	13.3	0.20	1.95	16.3
2.5	50 x 0.25	7.98	0.20	2.5	26.6
4	56 x 0.30	4.95	0.25	3.1	40.4
6	84 x 0.30	3.30	0.35	3.9	57.7
10	80 x 0.40	1.91	0.40	5.2	104
16	126 x 0.40	1.21	0.40	6.2	150
25	196 x 0.40	0.780	0.60	8.2	248
35	276 x 0.40	0.554	0.60	9.2	328
50	396 x 0.40	0.386	0.70	11.2	478

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* Nominal cross-section not available with the ref. EPFA.
** Nominal cross-sections not available with the ref. PFA.

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

**SILIFLON®
51YS****VDE approval**
-90 °C to +250 °C**Approvals - standards**

- VDE approval as per standard DIN VDE 0250 Part 106 - Licence no. 106489.

Applications

- Cabling in household electrical appliances, electronics.
 - Cabling in hot or cold environments (cryogenics).
- Cabling in aggressive environments (humidity, chemicals, etc.).
 - Cabling requiring compact size and excellent mechanical strength.

Options

- Flexible tin-plated copper core – ref. E51YS: contact us.
- Flexible nickel-plated copper core – ref. CN51YS: contact us.
- Flexible silver-plated copper core – ref. A51YS: contact us.
 - Solid bare copper core – ref. R51YS: see details of the option below.
- Solid tin-plated copper core – ref. RE51YS: contact us.
 - Rated voltage 450/750 V – ref. 51YA: contact us.

Characteristics**General**


- Continuous operating temperatures:
 - > Bare copper core: -90 °C to +130 °C.
 - > Tin-plated copper core: -90 °C to +180 °C.
 - > Silver-plated copper core: -90 °C to +200 °C.
 - > Nickel-plated copper core: -90 °C to +250 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 300/500 V.
- Test voltage: 2000 V.

Standard products

- All colours including translucent.



- 1 • Flexible bare copper core – class 5 as per IEC 60228 / DIN VDE 0295.
- 2 • Insulation: Fluorinated polymer PFA.

51YS**Flexible core • class 5 as per IEC 60228**

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.25*	19 x 0.13 or 7 x 0.22	79.9
0.5	16 x 0.20	39.0
0.75	24 x 0.20	26.0
1	32 x 0.20	19.5
1.5	30 x 0.25	13.3
2.5	50 x 0.25	7.98
4	56 x 0.30	4.95
6	84 x 0.30	3.30

INSULATED WIRES

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.30	1.25	4.2
0.30	1.5	6.5
0.30	1.65	8.7
0.30	1.8	10.9
0.30	2.0	14.9
0.35	2.6	25.0
0.40	3.4	41.9
0.40	3.9	60.1

Option • R51YS**Solid core • class 1 as per IEC 60228**

0.25*	1 x 0.56	74.5	0.30	1.15	3.9
0.5	1 x 0.80	36.0	0.30	1.4	6.8
0.75	1 x 0.98	23.1	0.30	1.6	9.5
1	1 x 1.13	18.1	0.30	1.75	12.0
1.5	1 x 1.36	12.1	0.30	2.0	16.7
2.5	1 x 1.77	7.41	0.35	2.5	27.4
4	1 x 2.24	4.61	0.40	3.05	42.7
6	1 x 2.74	3.08	0.40	3.55	61.7

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* Nominal cross-section not described in IEC 60228.

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON®

RETFE, RFEP and RPFA

-90 °C to +260 °C



Approvals - standards

- Series inspired by standard NF C 93-522.

Applications

- Cabling in household electrical appliances, electronics.
- Cabling in hot or cold environments (cryogenics).
- Cabling in aggressive environments (humidity, chemicals, etc.).
 - Cabling requiring compact size and excellent mechanical strength.

Options

- Solid tin-plated copper core
 - ref. REETFE, REFEP and REPPA: contact us.
- Solid silver-plated copper core
 - ref. RAETFE, RAFEP and RAPPA: contact us.
- Solid nickel-plated copper core
 - ref. RCNETFE, RCNFEP and RCNPFA: contact us.
- Solid pure nickel core
 - ref. RNETFE, RNFEF and RNPPA: contact us.

Characteristics

General

- Continuous operating temperatures:
 - RETFE: -90 °C to +155 °C.
 - RFEP: -90 °C to +205 °C.
 - RPFA: -90 °C to +260 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 300/500 V.
- Test voltage: 2500 V.

Standard products

- All colours including translucent.

RETFE, RFEP and RPFA

SOLID CORE

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.03	1 x 0.20	599
0.05	1 x 0.25	384
0.07	1 x 0.30	268
0.125	1 x 0.40	140
0.15	1 x 0.43	118
0.2	1 x 0.50	93.1
0.22	1 x 0.52	84.2
0.32*	1 x 0.64	57.5
0.5	1 x 0.80	36.0
0.75	1 x 0.98	24.5
1	1 x 1.13	18.1
1.5	1 x 1.36	12.1
2.5	1 x 1.77	7.41
4	1 x 2.24	4.61
6	1 x 2.74	3.08

INSULATED WIRE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.15	0.5	0.6
0.15	0.55	0.8
0.17	0.65	1.2
0.17	0.75	1.8
0.17	0.8	2.1
0.17	0.85	2.6
0.17	0.85	2.7
0.20	1.05	4.1
0.20	1.2	5.9
0.20	1.4	8.5
0.25	1.65	11.5
0.25	1.9	16.0
0.30	2.4	26.6
0.35	2.95	41.7
0.35	3.45	60.5

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

** Nominal cross-section available in the solid tin-plated copper core version only.

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® 105 °C

Fluoropolymer insulation

UL and cUL approval



- 1 • Bare, tin-plated, nickel-plated or silver-plated copper core.
- 2 • Insulation: Fluorinated polymer.

Approvals - standards

- UL approval as per standard UL 758 – File no.: E101965.
 - cUL approval (CSA) as per standard C22.2 No. 210 – File no.: E101965.
- “Horizontal flame test” as per UL approval.
- “FT1 flame rating” as per cUL approval.

Applications

- Cabling for household electrical heating appliances, small electric motors, electronic equipment, rear computer panels, etc.

Options

- Other nominal cross-sections: contact us.
 - Other style nos. available: styles no. 1226, 1517 and 1523.
- Style n° 1863 (125°C - 300 V): contact us.

Characteristics

General

- Continuous operating temperatures: -90 °C to +105 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- All colours including translucent.
- Stranding of conducting cores: contact us.

Style no.		1513		1227		1508		10101	
Insulation		ETFE “Thin-wall”		FEP		ETFE “Thin-wall”		ETFE	
Approval		105 °C - VNS		105 °C - VNS		105 °C - 30 V		105 °C - 250 V	
Nominal cross-section		Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)
AWG	(mm ²)								
30	0.05	0.13	0.55	0.20	0.7	0.14	0.6	0.25	0.8
28	0.09	0.13	0.65	0.20	0.8	0.14	0.7	0.25	0.9
26	0.13	0.13	0.75	0.20	0.9	0.14	0.75	0.25	1.0
24	0.22	0.13	0.85	0.20	1.0	0.14	0.9	0.25	1.1
22	0.34	0.13	1.0	0.20	1.15	0.14	1.05	0.25	1.25
-	0.5	0.13	1.2	0.20	1.3	0.14	1.2	0.25	1.35
20	0.6	0.13	1.25	0.20	1.4	0.14	1.3	0.25	1.45
-	0.75	-	-	0.33	1.75	-	-	-	-
18	0.93	-	-	0.33	1.9	-	-	-	-
-	1	-	-	0.33	1.95	-	-	-	-
16	1.34	-	-	0.33	2.2	-	-	-	-
-	1.5	-	-	0.33	2.2	-	-	-	-
14	-	-	-	0.33	2.6	-	-	-	-
-	2.5	-	-	0.33	2.7	-	-	-	-
12	-	-	-	0.33	3.2	-	-	-	-
-	4	-	-	0.33	3.25	-	-	-	-
10	-	-	-	0.33	3.9	-	-	-	-
-	6	-	-	0.33	3.9	-	-	-	-
Conducting metal		BCD		BCDEFG		BCD		BCD	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories. © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

OMERIN division Berne ✓
La Forie - F 63600 Ambert
Tel. +33 (0)4 73 82 03 81 - Fax +33 (0)4 73 82 18 69
berne@omerin.com



SILIFLON® style 10935

ETFE insulation + reinforcing braid

UL and cUL approval

-60 °C to +150 °C

Approvals - standards

- UL approval as per standard UL 758 – File no.: E101965.
- cUL approval as per standard C22.2 No. 210 (AWM I A/B FT1 FT2 150°C 600V) – File no.: E101965.
- CSA approval as per standard C22.2 No. 127 (Equipment and Lead Wire).
- "Horizontal flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.
- "FT2 flame rating" as per cUL approval.

Applications

- Internal cabling for electrical appliances or electronic appliances.

Options

- Other nominal stranding: contact us.
- Other colours: contact us.



- 1 • Bare or tin-plated copper core.
- 2 • Insulation: Fluorinated polymer ETFE.
- 3 • Reinforcement: Varnished synthetic fibre braid.

Characteristics General

- Continuous operating temperatures: -60 °C to +150 °C.
- Excellent resistance to solvents, impregnation varnish and other chemical influences.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 600 V.
- Test voltage: 6000 V.

Standard products

- Standard insulation colour: white.
- Standard reinforcing braid colours: white, blue, red, black, yellow or brown.

KEY

- Conducting metals
 - B Tin-plated copper
 - B* Tin-plated copper (ø > 0.38 mm)
 - C Nickel-plated copper
 - D Silver-plated copper
 - E Nickel
 - F Bare copper
 - F* Bare copper (ø > 0.38 mm)
 - G Nickel-plated copper 27 %
- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring
- NS Not Specified
- VNS Voltage Not Specified
- : UL approved nominal cross-sections only.

Style no.

10935

Approval

150 °C - 600 V AWM I A/B

AWG	Nominal cross-section (mm²)	Average thickness of insulation (mm)	Nominal diameter*		Approximate linear weight (kg/km)
			Multistrand core (mm)	Solid core (mm)	
24	0.22	0.15	1.2	1.15	3.2
22	0.34	0.15	1.3	1.2	4.3
-	0.5	0.15	1.5	1.4	6.1
20	0.6	0.15	1.6	-	6.8
-	0.75	0.20	1.7	1.65	8.9
18	0.93	0.20	1.85	1.7	10.1
-	1	0.20	2.0	1.9	11.5
16	1.34	0.20	2.2	2.0	15.0
-	1.5	0.20	2.25	2.1	16.0
14	-	0.33	2.8	2.6	22.4
-	2.5	0.33	3.1	2.9	26.4
12	-	0.33	3.4	-	38.2
-	4	0.33	3.6	3.3	38.6
10	-	0.33	4.1	-	56.0
-	6	0.33	4.2	4.0	56.1
8	-	0.51	5.2	-	91.5
-	10	0.51	6.0	-	107
6	-	0.51	6.8	-	143
-	16	0.51	7.1	-	160
4	-	0.51	8.1	-	220
-	25	0.51	8.6	-	249
2	35	0.51	9.7	-	331
1	-	0.76	11.3	-	443
-	50	0.76	11.7	-	478
1/0	-	0.76	12.4	-	545
2/0	70	0.76	13.5	-	659
3/0	-	0.76	15.1	-	838
-	95	0.76	15.2	-	855
4/0	-	0.76	16.7	-	1 045
-	120	0.76	16.9	-	1 094

Conducting metal

BF

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.




SILIFLON® style 11881

FEP insulation + reinforcing braid

UL and cUL approval

-60 °C to +200 °C



- 1 • Bare, tin-plated, nickel-plated or silver-plated copper core.
- 2 • Insulation: Fluorinated polymer FEP.
- 3 • Reinforcement: Varnished fiberglass braid.

Approvals - standards

- UL approval as per standard UL 758 – File no.: E101965.
- cUL approval as per standard C22.2 No. 210 (AWM I A/B FT1 FT2 200°C 600V) – File no.: E101965.
- “Horizontal flame test” as per UL approval.
- “FT1 flame rating” as per cUL approval.
- “FT2 flame rating” as per cUL approval.

Applications

- Internal cabling for electrical appliances or electronic appliances.

Options

- Other nominal stranding: contact us.
- Other colours: contact us.

Characteristics

General

- Continuous operating temperatures: -60 °C to +200 °C.
- Excellent resistance to solvents, impregnation varnish and other chemical influences.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 600 V.
- Test voltage: 6000 V.

Standard products

- Standard insulation colour: white.
- Standard reinforcing braid colours: white, blue, red, black, yellow or brown.

Style no.

11881

Approval

200 °C - 600 V
AWM I A/B

Nominal cross-section		Average thickness of insulation (mm)	Nominal diameter*		Approximate linear weight (kg/km)
AWG	(mm ²)		Multistrand core (mm)	Solid core (mm)	
24	0.22	0.15	1.2	1.15	3.2
22	0.34	0.15	1.3	1.2	4.3
-	0.5	0.15	1.5	1.4	6.1
20	0.6	0.15	1.6	-	6.8
-	0.75	0.20	1.7	1.65	8.9
18	0.93	0.20	1.85	1.7	10.1
-	1	0.20	2.0	1.9	11.5
16	1.34	0.20	2.2	2.0	15.0
-	1.5	0.20	2.25	2.1	16.0
14	-	0.33	2.8	2.6	22.4
-	2.5	0.33	3.1	2.9	26.4
12	-	0.33	3.4	-	38.2
-	4	0.33	3.6	3.3	38.6
10	-	0.33	4.1	-	56.0
-	6	0.33	4.2	4.0	56.1
8	-	0.51	5.2	-	91.5
-	10	0.51	6.0	-	107
6	-	0.51	6.8	-	143
-	16	0.51	7.1	-	160
4	-	0.51	8.1	-	220
-	25	0.51	8.6	-	249
2	35	0.51	9.7	-	331
1	-	0.76	11.3	-	443
-	50	0.76	11.7	-	478
1/0	-	0.76	12.4	-	545
2/0	70	0.76	13.5	-	659
3/0	-	0.76	15.1	-	838
-	95	0.76	15.2	-	855
4/0	-	0.76	16.7	-	1 045
-	120	0.76	16.9	-	1 094

Conducting metal: B*CDEF*G

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0,38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0,38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■ : UL approved nominal cross-sections only.

SILIFLON® 150 °C

Fluoropolymer insulation

UL and cUL approval



- 1 • Bare, tin-plated, nickel-plated or silver-plated copper core.
- 2 • Insulation: Fluorinated polymer.

Approvals - standards

- UL approval as per standard UL 758 – File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 – File no.: E101965.
- “Horizontal flame test” as per UL approval.
- “FT1 flame rating” as per cUL approval.
- VW-1 approval for Style 1333, Style 10126 and Style 11945 (AWG 24 to 18 Cross-sections).

Characteristics General

- Continuous operating temperatures: -90 °C to +150 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- All colours including translucent.
- Stranding of conducting cores: contact us.

Applications

- Cabling for household electrical heating appliances, rotating machines, industrial machines, electronic equipment, rear computer panels, etc.

Options

- Other nominal cross-sections: contact us.
- Other style nos. available: styles no. 1591, 1814, 1829, 1857, 1858, 1859, 11537, 10211.

Style no. 1827

Insulation ETFE “Thin-wall”
Approval

10125

ETFE “Thin-wall”

1828

ETFE

1643

ETFE

150 °C – 125 V			150 °C – 300 V		150 °C – 300 V		150 °C – 300 V	
Nominal cross-section	Average thickness of insulation (mm)	Nominal diameter*	Average thickness of insulation (mm)	Nominal diameter*	Average thickness of insulation (mm)	Nominal diameter*	Average thickness of insulation (mm)	Nominal diameter*
30	0.05	0.14	0.13	0.6	0.33	0.95	0.33	0.95
28	0.09	0.14	0.7	0.15	0.7	1.05	0.33	1.05
26	0.13	0.14	0.75	0.15	0.75	1.15	0.33	1.15
24	0.22	0.14	0.9	0.15	0.9	1.3	0.33	1.3
22	0.34	0.14	1.05	0.15	1.05	1.4	0.33	1.4
-	0.5	0.14	1.2	0.15	1.25	1.6	0.33	1.6
20	0.6	0.14	1.3	0.15	1.3	1.65	0.33	1.65
-	0.75	0.20	1.5	0.15	1.4	1.75	0.33	1.75
18	0.93	0.20	1.65	0.15	1.55	1.9	0.33	1.9
-	1	0.20	1.7	0.15	1.65	1.95	0.33	1.95
16	1.34	0.20	1.9	0.20	1.9	2.2	0.33	2.2
-	1.5	0.20	1.9	0.20	1.9	2.2	0.33	2.2
14	-	0.33	2.55	0.20	2.5	2.55	0.33	2.55
-	2.5	0.33	2.7	0.20	2.45	2.7	0.33	2.7
12	-	0.33	3.1	0.25	2.9	3.1	0.33	3.0
-	4	0.33	3.25	0.25	3.1	3.25	0.33	3.25
10	-	0.33	3.7	0.25	3.6	3.7	0.33	3.9
-	6	0.33	3.9	0.25	3.7	3.9	0.33	3.9
8	-	-	-	0.64	5.4	-	0.51	5.3
-	10	-	-	0.64	5.7	-	0.51	5.4
6	-	-	-	0.64	6.6	-	0.51	6.3
-	16	-	-	0.64	6.7	-	0.51	6.6
4	-	-	-	0.64	7.8	-	0.51	7.4
-	25	-	-	0.64	8.3	-	0.51	8.0
2	35	-	-	0.89	10.0	-	0.51	9.3
1	-	-	-	0.89	11.0	-	0.76	10.7
-	50	-	-	0.89	11.4	-	0.76	11.1
1/0	-	-	-	1.14	12.5	-	0.76	11.7
2/0	70	-	-	1.14	14.0	-	0.76	12.8
3/0	-	-	-	1.14	15.2	-	0.76	14.4
-	95	-	-	1.14	15.4	-	0.76	14.6
4/0	-	-	-	1.14	16.8	-	0.76	16.0
-	120	-	-	1.14	17.1	-	0.76	16.3

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com



www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Style no. Insulation Approval		1333-VW-1 FEP 150 °C – 300 V		10210 ETFE "Thin-wall" 150 °C – 600 V		10126-VW-1 ETFE "Thin-wall" 150 °C – 600 V		1644 ETFE 150 °C – 600 V		1331 FEP 150 °C – 600 V		11945 ETFE "Thin-wall" 150 °C – 750 V		10358 ETFE 150 °C – 1000 V (cUL 600 V)	
Nominal cross-section		Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)
30	0.05	0.33	0.95	-	-	0.25	0.8	0.51	1.3	0.51	1.3	-	-	0.51	1.3
28	0.09	0.33	1.05	-	-	0.25	0.9	0.51	1.4	0.51	1.4	-	-	0.51	1.4
26	0.13	0.33	1.15	-	-	0.25	1.05	0.51	1.5	0.51	1.5	-	-	0.51	1.5
24	0.22	0.33	1.3	0.15	0.9	0.25	1.15	0.51	1.65	0.51	1.65	0.15	0.9	0.51	1.65
22	0.34	0.33	1.4	0.15	1.05	0.25	1.3	0.51	1.8	0.51	1.8	0.15	1.05	0.51	1.8
-	0.5	0.33	1.6	0.15	1.25	0.25	1.4	0.51	1.95	0.51	1.95	0.15	1.25	0.51	1.95
20	0.6	0.33	1.65	0.15	1.35	0.25	1.5	0.51	2.0	0.51	2.0	0.15	1.35	0.51	2.0
-	0.75	0.33	1.75	0.15	1.4	0.25	1.55	0.51	2.1	0.51	2.1	0.15	1.4	0.51	2.1
18	0.93	0.33	1.9	0.15	1.55	0.25	1.8	0.51	2.25	0.51	2.25	0.15	1.55	0.51	2.25
-	1	0.33	1.95	0.15	1.65	0.25	1.8	0.51	2.3	0.51	2.3	0.15	1.65	0.51	2.3
16	1.34	0.33	2.2	0.20	1.9	0.25	2.0	0.51	2.5	0.51	2.5	0.20	1.9	0.51	2.5
-	1.5	0.33	2.2	0.20	1.9	0.25	2.0	0.51	2.55	0.51	2.55	0.20	1.9	0.51	2.55
14	-	0.33	2.55	0.20	2.25	0.25	2.4	0.51	2.85	0.51	2.85	0.20	2.25	0.51	2.85
-	2.5	0.33	2.7	0.20	2.45	0.25	2.45	0.51	3.0	0.51	3.0	0.20	2.45	0.51	3.0
12	-	0.33	3.1	0.25	2.9	0.38	3.2	0.51	3.25	0.51	3.3	0.25	2.9	0.51	3.3
-	4	0.33	3.25	0.25	3.1	0.38	3.35	0.51	3.6	0.51	3.6	0.25	3.1	0.51	3.6
10	-	0.33	3.7	0.25	3.6	0.38	4.1	0.51	4.1	0.51	4.1	0.25	3.6	0.51	4.1
-	6	0.33	3.9	-	-	0.38	4.5	0.51	4.3	0.51	4.3	-	-	0.51	4.3
8	-	-	-	-	-	0.64	5.4	0.76	5.6	0.76	5.4	-	-	0.76	5.4
-	10	-	-	-	-	0.64	5.7	0.76	5.9	0.76	5.9	-	-	0.76	5.9
6	-	-	-	-	-	0.64	6.6	0.76	6.8	0.76	6.8	-	-	0.76	6.8
-	16	-	-	-	-	0.64	6.7	0.76	7.1	0.76	7.1	-	-	0.76	7.1
4	-	-	-	-	-	0.64	7.8	0.76	8.0	0.76	8.0	-	-	0.76	8.0
-	25	-	-	-	-	0.64	8.3	0.76	8.5	0.76	8.5	-	-	0.76	8.5
2	35	-	-	-	-	0.89	10.0	0.76	9.6	0.76	9.6	-	-	0.76	9.6
1	-	-	-	-	-	0.89	11.0	1.14	11.2	1.14	11.2	-	-	1.14	11.2
-	50	-	-	-	-	0.89	11.4	1.14	12.0	1.14	12.0	-	-	1.14	12.0
1/0	-	-	-	-	-	1.14	12.5	1.14	12.5	1.14	12.5	-	-	1.14	12.5
2/0	70	-	-	-	-	1.14	14.0	1.14	14.6	1.14	14.0	-	-	1.14	14.0
3/0	-	-	-	-	-	1.14	15.2	1.14	15.2	1.14	15.2	-	-	1.14	15.2
-	95	-	-	-	-	1.14	15.4	1.14	15.4	1.14	15.4	-	-	1.14	15.4
4/0	-	-	-	-	-	1.14	16.8	1.14	16.8	1.14	16.8	-	-	1.14	16.8
-	120	-	-	-	-	1.14	17.1	1.14	17.1	1.14	17.1	-	-	1.14	17.1
Conducting metal		BCDEFG		BCDEFG		BCDEFG		BCDEFG		BCDEFG		BCDEFG		BCDEFG	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

For this product, please contact:

OMERIN division principale ✓
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® 200 °C

Fluoropolymer insulation

UL and cUL approval



- 1 • Bare, tin-plated, nickel-plated or silver-plated copper core.
- 2 • Insulation: Fluorinated polymer.

Approvals - standards

- UL approval as per standard UL 758 – File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 – File no.: E101965.
- “Horizontal flame test” as per UL approval.
- “FT1 flame rating” as per cUL approval.
- VW-1 approval for Style 1330 and 1332.

Characteristics General

- Continuous operating temperatures: -90 °C to +200 °C.
- Excellent resistance to aggressive chemical environments.
 - Excellent resistance to humidity and UV.
 - Excellent mechanical strength.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- All colours including translucent.
- Stranding of conducting cores: contact us.

Applications

- Cabling for household electrical heating appliances, rotating machines, industrial machines, electronic equipment, rear computer panels, etc.

Options

- Other nominal cross-sections: contact us.

Style no. Insulation Approval	10109 ETFE "Thin-wall"		10969 FEP		1900 FEP		1332-VW-1 FEP "Thick-wall"	
	200 °C – 300 V		200 °C – 300 V		200 °C – 300 V		200 °C – 300 V	
Nominal cross-section	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)
AWG (mm²)								
30 (0.05)	0.15	0.6	0.20	0.7	0.25	0.8	0.33	0.95
28 (0.09)	0.15	0.7	0.20	0.8	0.25	0.9	0.33	1.05
26 (0.13)	0.15	0.8	0.20	0.9	0.25	1.0	0.33	1.15
24 (0.22)	0.15	0.9	0.20	1.0	0.25	1.1	0.33	1.3
22 (0.34)	0.15	1.05	0.20	1.15	0.25	1.25	0.33	1.45
- (0.5)	0.15	1.25	0.20	1.3	0.25	1.4	0.33	1.55
20 (0.6)	0.15	1.3	0.20	1.4	0.25	1.5	0.33	1.7
- (0.75)	0.15	1.4	0.33	1.75	0.25	1.55	0.33	1.75
18 (0.93)	0.15	1.55	0.33	1.9	0.25	1.7	0.33	1.9
- (1)	0.15	1.65	0.33	1.95	0.25	1.8	0.33	1.95
16 (1.34)	0.20	1.9	0.33	2.1	0.25	2.0	0.33	2.1
- (1.5)	0.20	1.9	0.33	2.2	0.25	2.0	0.33	2.2
14 (-)	0.20	2.25	0.33	2.5	0.25	2.4	0.33	2.7
- (2.5)	0.20	2.45	0.33	2.7	0.25	2.55	0.33	2.7
12 (-)	0.25	2.9	0.33	3.2	0.25	2.9	0.33	3.2
- (4)	0.25	3.1	0.33	3.25	0.25	3.1	0.33	3.25
10 (-)	0.25	3.6	0.33	3.9	0.25	3.6	0.33	3.9
- (6)	0.25	3.7	0.33	3.9	0.25	3.7	0.33	3.9
8 (-)	0.64	5.4	-	-	-	-	-	-
- (10)	0.64	5.7	-	-	-	-	-	-
6 (-)	0.64	6.6	-	-	-	-	-	-
- (16)	0.64	6.7	-	-	-	-	-	-
4 (-)	0.64	7.8	-	-	-	-	-	-
- (25)	0.64	8.3	-	-	-	-	-	-
2 (35)	0.89	10.0	-	-	-	-	-	-
1 (-)	0.89	11.0	-	-	-	-	-	-
- (50)	0.89	11.4	-	-	-	-	-	-
1/0 (-)	1.14	12.5	-	-	-	-	-	-
2/0 (-)	1.14	14.0	-	-	-	-	-	-
3/0 (-)	1.14	15.2	-	-	-	-	-	-
- (95)	1.14	15.4	-	-	-	-	-	-
4/0 (-)	1.14	16.8	-	-	-	-	-	-
- (120)	1.14	17.1	-	-	-	-	-	-
Conducting metal	B*CDEF*G		B*CDEF*G		B*CDEG		B*CDEF*G	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickelplated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

For this product, please contact:

OMERIN division principale
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com



www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Style no. Insulation Approval		10086 ETFE "Thin-wall"		10588 FEP "Thin-wall"		1901 FEP		1330-VW-1 FEP "Thick-wall"		1930 PEA "Thick-wall"		10203 FEP		10048 FEP "Thick-wall"	
200 °C – 600 V		200 °C – 600 V		200 °C – 600 V		200 °C – 600 V		200 °C – 600 V		200 °C – 600 V		200 °C – 1 000 V		200 °C – 1 000 V	
Nominal cross-section		Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*
AWG	(mm²)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)
30	0.05	0.25	0.8	0.23	0.75	0.36	1.0	0.51	1.3	0.51	1.3	0.51	1.3	0.64	1.6
28	0.09	0.25	0.9	0.23	0.85	0.36	1.1	0.51	1.4	0.51	1.4	0.51	1.4	0.64	1.7
26	0.13	0.25	1.0	0.23	0.95	0.36	1.2	0.51	1.5	0.51	1.5	0.51	1.5	0.64	1.8
24	0.22	0.25	1.1	0.23	1.05	0.36	1.35	0.51	1.65	0.51	1.65	0.51	1.65	0.64	1.9
22	0.34	0.25	1.25	0.23	1.2	0.36	1.45	0.51	1.85	0.51	1.8	0.51	1.8	0.64	2.05
-	0.5	0.25	1.4	0.23	1.35	0.36	1.65	0.51	1.95	0.51	1.95	0.51	1.95	0.64	2.2
20	0.6	0.25	1.5	0.23	1.45	0.36	1.7	0.51	2.0	0.51	2.0	0.51	2.0	0.64	2.3
-	0.75	0.25	1.55	0.23	1.5	0.36	1.8	0.51	2.1	0.51	2.1	0.51	2.1	0.64	2.4
18	0.93	0.25	1.7	0.23	1.65	0.36	2.0	0.51	2.25	0.51	2.25	0.51	2.25	0.64	2.55
-	1	0.25	1.8	0.23	1.75	0.36	2.0	0.51	2.3	0.51	2.3	0.51	2.3	0.64	2.6
16	1.34	0.25	2.0	0.23	1.95	0.36	2.2	0.51	2.5	0.51	2.55	0.51	2.5	0.64	2.8
-	1.5	0.25	2.0	0.23	1.95	0.36	2.3	0.51	2.55	0.51	2.55	0.51	2.55	0.64	2.85
14	-	0.25	2.4	0.23	2.35	0.36	2.6	0.51	3.0	0.51	3.0	0.51	3.0	0.64	3.2
-	2.5	0.25	2.55	0.23	2.5	0.36	2.75	0.51	3.0	0.51	3.0	0.51	3.0	0.64	3.3
12	-	0.38	3.2	0.23	2.9	0.36	3.1	0.51	3.4	0.51	3.4	0.51	3.4	0.64	3.6
-	4	0.38	3.35	0.23	3.1	0.36	3.3	0.51	3.6	0.51	3.6	0.51	3.6	0.64	3.9
10	-	0.38	3.8	0.23	3.5	0.36	3.8	0.51	4.0	0.51	4.0	0.51	4.0	0.64	4.3
-	6	0.38	4.0	-	-	0.36	4.0	0.51	4.3	0.51	4.3	0.51	4.3	0.64	4.5
8	-	0.64	5.4	-	-	0.51	5.2	0.76	5.3	0.76	5.6	0.76	5.6	-	-
-	10	0.64	5.7	-	-	0.51	5.4	0.76	5.9	0.76	5.9	0.76	5.9	-	-
6	-	0.64	6.6	-	-	0.51	6.3	0.76	6.8	0.76	6.8	0.76	6.8	-	-
-	16	0.64	6.7	-	-	0.51	6.6	0.76	7.1	0.76	7.1	0.76	7.1	-	-
4	-	0.64	7.8	-	-	0.51	7.4	0.76	8.0	0.76	8.0	0.76	8.0	-	-
-	25	0.64	8.3	-	-	0.51	8.0	0.76	8.5	0.76	8.5	0.76	8.5	-	-
2	35	0.89	10.0	-	-	0.51	9.3	0.76	9.2	0.76	9.2	0.76	9.2	-	-
1	-	0.89	11.0	-	-	0.76	10.7	1.14	11.2	1.14	11.2	1.14	11.2	-	-
-	50	0.89	11.4	-	-	0.76	11.1	1.14	12.0	1.14	12.0	1.14	12.0	-	-
1/0	-	1.14	12.5	-	-	0.76	11.7	1.14	12.5	1.14	12.5	1.14	12.5	-	-
2/0	70	1.14	14.0	-	-	0.76	12.8	1.14	14.0	1.14	14.0	1.14	14.0	-	-
3/0	-	1.14	15.2	-	-	0.76	14.4	1.14	15.2	1.14	15.2	1.14	15.2	-	-
-	95	1.14	15.4	-	-	0.76	14.6	1.14	15.4	1.14	15.4	1.14	15.4	-	-
4/0	-	1.14	16.8	-	-	0.76	16.0	1.14	16.8	1.14	16.8	1.14	16.8	-	-
-	120	1.14	17.1	-	-	0.76	16.3	1.14	17.1	1.14	17.1	1.14	17.1	-	-
Conducting metal		B*CDEF*G		B*CDEF*G		B*CDEF*G		B*CDEF*G		B*CDEF*G		B*CDEF*G		B*CDEG	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

For this product, please contact:

OMERIN division principale ✓
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® 250 °C

Fluoropolymer insulation

UL and cUL approval



- 1 • Bare, tin-plated, nickel-plated or silver-plated copper core.
- 2 • Insulation: Fluorinated polymer.

Approvals - standards

- UL approval as per standard UL 758 – File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 – File no.: E101965.
- “Horizontal flame test” as per UL approval.
- “FT1 flame rating” as per cUL approval.
- VW-1 approval for Style 1727.

Characteristics General

- Continuous operating temperatures: -90 °C to +250 °C.
- Excellent resistance to aggressive chemical environments.
 - Excellent resistance to humidity and UV.
 - Excellent mechanical strength.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- All colours including translucent.
- Stranding of conducting cores: contact us.

Applications

- Cabling for household electrical heating appliances, rotating machines, industrial machines, electronic equipment, rear computer panels, etc.

Options

- Other nominal cross-sections: contact us.

Style no. Insulation Approval	1933 PFA "Thin-wall"		1882 PFA		10486 PFA	
	250 °C - VNS		250 °C - 150 V		250 °C - 300 V	
Nominal cross-section	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)
30	0.05	0.15	0.25	0.8	0.23	0.75
28	0.09	0.15	0.25	0.9	0.23	0.85
26	0.13	0.15	0.25	1.0	0.23	0.95
24	0.22	0.15	0.25	1.1	0.23	1.1
22	0.34	0.15	0.25	1.25	0.23	1.2
-	0.5	0.15	0.25	1.4	0.23	1.4
20	0.6	0.15	0.25	1.5	0.23	1.5
-	0.75	-	0.25	1.55	0.23	1.55
18	0.93	-	0.25	1.8	0.23	1.75
-	1	-	0.25	1.8	0.23	1.75
16	1.34	-	0.25	2.0	0.23	2.0
-	1.5	-	0.25	2.0	0.23	2.0
14	-	-	-	-	0.23	2.3
-	2.5	-	-	-	0.23	2.5
12	-	-	-	-	0.23	2.8
-	4	-	-	-	0.23	3.05
10	-	-	-	-	0.23	3.6
-	6	-	-	-	0.23	3.65
8	-	-	-	-	0.51	5.2
-	10	-	-	-	0.51	5.4
6	-	-	-	-	0.51	6.3
-	16	-	-	-	0.51	6.6
4	-	-	-	-	0.76	8.0
-	25	-	-	-	0.76	8.5
2	35	-	-	-	0.76	9.6
1	-	-	-	-	1.14	11.2
-	50	-	-	-	1.14	12.0
1/0	-	-	-	-	1.14	12.5
2/0	70	-	-	-	1.14	14.0
3/0	-	-	-	-	1.14	15.2
-	95	-	-	-	1.14	15.4
4/0	-	-	-	-	1.14	16.8
-	120	-	-	-	1.14	17.1
Conducting metal	CEG		CEG		CEG	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

For this product, please contact:

OMERIN division principale
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Style no. Insulation Approval	10410 MFA 250 °C – 300 V		1726 PFA 250 °C – 300 V		10297 MFA "Thin-wall" 250 °C – 600 V		10362 PFA "Thin-wall" 250 °C – 600 V		1727-VW-1 PFA 250 °C – 600 V		10300 MFA 250 °C – 600 V		10371 PFA "Thin-wall" 250 °C – 1000 V (cUL 600 V)		
	Nominal cross-section	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*
AWG	(mm²)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)
30	0.05	0.25	0.8	0.33	0.95	-	-	0.25	0.8	0.51	1.3	0.51	1.3	0.51	1.3
28	0.09	0.25	0.9	0.33	1.05	0.25	0.9	0.25	0.9	0.51	1.4	0.51	1.4	0.51	1.4
26	0.13	0.25	1.0	0.33	1.15	0.25	1.0	0.25	1.0	0.51	1.5	0.51	1.5	0.51	1.5
24	0.22	0.25	1.1	0.33	1.3	0.25	1.1	0.25	1.1	0.51	1.65	0.51	1.65	0.51	1.65
22	0.34	0.25	1.25	0.33	1.45	0.25	1.25	0.25	1.25	0.51	1.8	0.51	1.8	0.51	1.8
-	0.5	0.25	1.4	0.33	1.6	0.25	1.4	0.25	1.4	0.51	1.95	0.51	1.95	0.51	1.95
20	0.6	0.25	1.5	0.33	1.65	0.25	1.5	0.25	1.5	0.51	2.0	0.51	2.0	0.51	2.0
-	0.75	0.25	1.55	0.33	1.75	0.25	1.55	0.25	1.55	0.51	2.1	0.51	2.1	0.51	2.1
18	0.93	0.25	1.8	0.33	1.9	0.25	1.8	0.25	1.8	0.51	2.2	0.51	2.2	0.51	2.2
-	1	0.25	1.8	0.33	1.95	0.25	1.8	0.25	1.8	0.51	2.3	0.51	2.3	0.51	2.3
16	1.34	0.25	2.0	0.33	2.2	0.25	2.0	0.25	2.0	0.51	2.45	0.51	2.45	0.51	2.45
-	1.5	0.25	2.0	0.33	2.2	0.25	2.0	0.25	2.0	0.51	2.65	0.51	2.5	0.51	2.55
14	-	0.25	2.4	0.33	2.6	0.25	2.4	0.25	2.4	0.51	2.85	0.51	2.85	0.51	2.8
-	2.5	0.25	2.55	0.33	2.7	0.25	2.55	0.25	2.55	0.51	3.0	0.51	3.0	0.51	3.0
12	-	0.25	2.9	0.33	3.2	0.25	2.9	0.25	2.9	0.51	3.4	0.51	3.4	0.51	3.4
-	4	0.25	3.1	0.33	3.25	0.25	3.1	0.25	3.1	0.51	3.6	0.51	3.6	0.51	3.6
10	-	0.25	3.6	0.33	3.9	0.25	3.6	0.25	3.6	0.51	4.2	0.51	4.2	0.51	4.2
-	6	0.25	3.7	0.33	3.9	0.25	3.7	0.25	3.7	0.51	4.3	0.51	4.3	0.51	4.3
8	-	-	-	0.51	5.2	0.25	4.6	0.76	5.8	0.76	5.7	0.76	5.7	0.76	5.7
-	10	-	-	0.51	5.4	0.25	4.9	0.76	5.9	0.76	5.9	0.76	5.9	0.76	5.9
6	-	-	-	0.51	6.3	0.25	5.8	0.76	6.8	0.76	6.8	0.76	6.8	0.76	6.8
-	16	-	-	0.51	6.6	0.25	6.1	0.76	7.1	0.76	7.1	0.76	7.1	0.76	7.1
4	-	-	-	0.76	8.0	0.25	6.9	0.76	8.0	0.76	8.0	0.76	8.0	0.76	8.0
-	25	-	-	0.76	8.5	0.25	7.5	0.76	8.5	0.76	8.5	0.76	8.5	0.76	8.5
2	35	-	-	0.76	9.6	-	-	0.76	9.6	0.76	9.6	0.76	9.6	0.76	9.6
1	-	-	-	1.14	11.2	-	-	1.14	11.2	1.14	11.2	1.14	11.2	1.14	11.2
-	50	-	-	1.14	12.0	-	-	1.14	12.0	1.14	12.0	1.14	12.0	1.14	12.0
1/0	-	-	-	1.14	12.5	-	-	1.14	12.5	1.14	12.5	1.14	12.5	1.14	12.5
2/0	70	-	-	1.14	14.0	-	-	1.14	14.0	1.14	14.0	1.14	14.0	1.14	14.0
3/0	-	-	-	1.14	15.2	-	-	1.14	15.2	1.14	15.2	1.14	15.2	1.14	15.2
-	95	-	-	1.14	15.4	-	-	1.14	15.4	1.14	15.4	1.14	15.4	1.14	15.4
4/0	-	-	-	1.14	16.8	-	-	1.14	16.8	1.14	16.8	1.14	16.8	1.14	16.8
-	120	-	-	1.14	17.1	-	-	1.14	17.1	1.14	17.1	1.14	17.1	1.14	17.1
Conducting metal	CEG	CEG	CEG	CEG	CEG	CEG	CEG	CEG	CEG	CEG	CEG	CEG	CEG	CEG	CEG

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

For this product, please contact:

OMERIN division principale ✓
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® KZ 04

-55 °C to +200 °C



- 1 • Concentric silver-plated copper core.
- 2 • Insulation: PTFE tape(s).

Approvals - standards

- Inspired from NF C 93-523 standard.

Applications

- Wires used in aeronautical and electronic applications and all instrumentation uses requiring excellent resistance to high temperatures and to chemical influences.

Options

- Compliance with the American standard ANSI NEMA HP3: contact us.

Characteristics

General

- Continuous operating temperatures: -55 °C to +200 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity.
- Excellent resistance to hydrocarbons and fluids.

Electrical (as per UTE C 93-523)

- Rated voltage: 250 Vac – 350 Vdc.
- Test voltage: 2500 V.

Standard products

- Standard insulation colours: all solid colours.

KZ 04

CONCENTRIC CORE

Nominal cross-section AWG	(mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
32	0.035	7 x 0.08	546
30	0.055	7 x 0.10	349
28	0.093	7 x 0.13	201
26	0.14	7 x 0.16	132
24	0.22	7 x 0.20	86
22	0.34	7 x 0.25	54.4
20	0.60	19 x 0.20	31.3

INSULATED WIRE

Nominal diameter (mm)	Approximate linear weight (kg/km)
0.53	0.7
0.61	1.0
0.68	1.4
0.79	2.0
0.91	2.8
1.06	4.1
1.35	7.3

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® KZ 05

-55 °C to +200 °C



- 1 • Concentric silver-plated copper core.
- 2 • Insulation: PTFE tape(s).

Approvals - standards

- Inspired from NF C 93-523 standard.

Applications

- Wires used in aeronautical and electronic applications and all instrumentation uses requiring excellent resistance to high temperatures and to chemical influences.

Options

- Compliance with the American standard ANSI NEMA HP3: contact us.

Characteristics

General

- Continuous operating temperatures: -55 °C to +200 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity.
- Excellent resistance to hydrocarbons and fluids.

Electrical (as per UTE C 93-523)

- Rated voltage: 600 Vac – 850 Vdc.
- Test voltage: 3400 V.

Standard products

- Standard insulation colours: all solid colours.

KZ 05

CONCENTRIC CORE

Nominal cross-section AWG	(mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
32	0.035	7 x 0.08	546
30	0.055	7 x 0.10	349
28	0.093	7 x 0.13	201
26	0.14	7 x 0.16	132
24	0.22	7 x 0.20	86
22	0.34	7 x 0.25	54.4
20	0.60	19 x 0.20	31.3
18	0.93	19 x 0.25	20.5
16	1.34	19 x 0.30	13.9
14	1.91	27 x 0.30*	10
12	3.18	45 x 0.30*	6

INSULATED WIRE

Nominal diameter (mm)	Approximate linear weight (kg/km)
0.73	1.3
0.81	1.5
0.90	2.0
1.00	2.6
1.13	3.6
1.27	5.0
1.52	7.8
1.80	11.6
2.10	16.5
2.48	22.3
3.06	35.7

* Non-concentric cores.

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® KZ 06**-55 °C to +200 °C**

- 1 • Concentric silver-plated copper core.
- 2 • Insulation: PTFE tape(s).

Approvals - standards

- Inspired from NF C 93-523 standard.

Applications

- Wires used in aeronautical and electronic applications and all instrumentation uses requiring excellent resistance to high temperatures and to chemical influences.

Options

- Compliance with the American standard ANSI NEMA HP3: contact us.

Characteristics**General**

- Continuous operating temperatures: -55 °C to +200 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity.
- Excellent resistance to hydrocarbons and fluids.

Electrical (as per UTE C 93-523)

- Rated voltage: 1000 Vac – 1400 Vdc.
- Test voltage: 5000 V.

Standard products

- Standard insulation colours: all solid colours.

KZ 06**CONCENTRIC CORE**

Nominal cross-section AWG	(mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
32	0.035	7 x 0.08	546
30	0.055	7 x 0.10	349
28	0.093	7 x 0.13	201
26	0.14	7 x 0.16	132
24	0.22	7 x 0.20	86
22	0.34	7 x 0.25	54.4
20	0.60	19 x 0.20	31.3
18	0.93	19 x 0.25	20.5
16	1.34	19 x 0.30	13.9
14	1.91	27 x 0.30*	10
12	3.18	45 x 0.30*	6

INSULATED WIRE

Nominal diameter (mm)	Approximate linear weight (kg/km)
0.99	2.3
1.05	2.5
1.14	3.0
1.24	3.7
1.37	4.7
1.53	6.2
1.76	9.1
2.05	12.6
2.25	17.1
2.70	25.3
3.35	38.7

* Non-concentric cores.

For this product, please contact:

OMERIN division principale ✓

Zone Industrielle - F 63600 Ambert

Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10

omerin@omerin.com

omerin
LES CABLES DE L'EXTREME

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® KZ 07**-55 °C to +260 °C**

- 1 • Concentric nickel-plated copper core.
- 2 • Insulation: PTFE tape(s).

Approvals - standards

- Inspired from NF C 93-523 standard.

Applications

- Wires used in aeronautical and electronic applications and all instrumentation uses requiring excellent resistance to high temperatures and to chemical influences.

Options

- Compliance with the American standard ANSI NEMA HP3: contact us.

Characteristics**General**

- Continuous operating temperatures: -55 °C to +260 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity.
- Excellent resistance to hydrocarbons and fluids.

Electrical (as per UTE C 93-523)

- Rated voltage: 250 Vac – 350 Vdc.
- Test voltage: 2500 V.

Standard products

- Standard insulation colours: all solid colours.

KZ 07**CONCENTRIC CORE**

Nominal cross-section AWG	Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
32	0.035	7 x 0.08	612
30	0.055	7 x 0.10	391
28	0.093	7 x 0.13	225
26	0.14	7 x 0.16	148
24	0.22	7 x 0.20	96.5
22	0.34	7 x 0.25	60.8
20	0.60	19 x 0.20	35

INSULATED WIRE

Nominal diameter (mm)	Approximate linear weight (kg/km)
0.53	0.7
0.61	1.0
0.68	1.4
0.79	2.0
0.91	2.8
1.06	4.1
1.35	7.3

For this product, please contact:

OMERIN division principale

Zone Industrielle - F 63600 Ambert

Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10

omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® KZ 08**-55 °C to +260 °C**

- 1 • Concentric nickel-plated copper core.
- 2 • Insulation: PTFE tape(s).

Approvals - standards

- Inspired from NF C 93-523 standard.

Applications

- Wires used in aeronautical and electronic applications and all instrumentation uses requiring excellent resistance to high temperatures and to chemical influences.

Options

- Compliance with the American standard ANSI NEMA HP3: contact us.

Characteristics**General**

- Continuous operating temperatures: -55 °C to +260 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity.
- Excellent resistance to hydrocarbons and fluids.

Electrical (as per UTE C 93-523)

- Rated voltage: 600 Vac – 850 Vdc.
- Test voltage: 3400 V.

Standard products

- Standard insulation colours: all solid colours.

KZ 08**CONCENTRIC CORE**

Nominal cross-section AWG	Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
32	0.035	7 x 0.08	612
30	0.055	7 x 0.10	391
28	0.093	7 x 0.13	225
26	0.14	7 x 0.16	148
24	0.22	7 x 0.20	96.5
22	0.34	7 x 0.25	60.8
20	0.60	19 x 0.20	35
18	0.93	19 x 0.25	23
16	1.34	19 x 0.30	15.6
14	1.91	27 x 0.30*	11.2
12	3.18	45 x 0.30*	6.7

INSULATED WIRE

Nominal diameter (mm)	Approximate linear weight (kg/km)
0.73	1.3
0.81	1.5
0.90	2.0
1.00	2.6
1.13	3.6
1.27	5.0
1.52	7.8
1.80	11.6
2.10	16.5
2.48	22.3
3.06	35.7

* Non-concentric cores.

For this product, please contact:

OMERIN division principale ✓

Zone Industrielle - F 63600 Ambert

Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10

omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® KZ 09**-55 °C to +260 °C**

- 1 • Concentric nickel-plated copper core.
- 2 • Insulation: PTFE tape(s).

Approvals - standards

- Inspired from NF C 93-523 standard.

Applications

- Wires used in aeronautical and electronic applications and all instrumentation uses requiring excellent resistance to high temperatures and to chemical influences.

Options

- Compliance with the American standard ANSI NEMA HP3: contact us.

Characteristics**General**

- Continuous operating temperatures: -55 °C to +260 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity.
- Excellent resistance to hydrocarbons and fluids.

Electrical (as per UTE C 93-523)

- Rated voltage: 1000 Vac – 1400 Vdc.
- Test voltage: 5000 V.

Standard products

- Standard insulation colours: all solid colours.

KZ 09**CONCENTRIC CORE**

Nominal cross-section AWG	Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
30	0.055	7 x 0.10	391
28	0.093	7 x 0.13	225
26	0.14	7 x 0.16	148
24	0.22	7 x 0.20	96.5
22	0.34	7 x 0.25	60.8
20	0.60	19 x 0.20	35
18	0.93	19 x 0.25	23
16	1.34	19 x 0.30	15.6
14	1.91	27 x 0.30*	11.2
12	3.18	45 x 0.30*	6.7

INSULATED WIRE

Nominal diameter (mm)	Approximate linear weight (kg/km)
0.99	2.3
1.05	2.5
1.14	3.0
1.24	3.7
1.37	4.7
1.53	6.2
1.76	9.1
2.05	12.6
2.25	17.1
2.70	25.3
3.35	38.7

* Non-concentric cores.

For this product, please contact:

OMERIN division principale ✓

Zone Industrielle - F 63600 Ambert

Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10

omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.

For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® CN5YS and A5YS

VDE approval
-90 °C to +250 °C

Approvals - standards

- VDE approval as per standard DIN VDE 0250 Part 106 - Licence no. 40005809.



Applications

- Cabling in household electrical appliances, electronics.
 - Lighting, lights
- Cabling in hot or very cold environments (cryogenics).
 - Cabling in aggressive environments (humidity, chemicals, etc.).
 - Cabling requiring compact size and excellent mechanical strength.

Options

- Other colours: contact us.
- Other cores available:
 - Rigid nickel-plated (ref. RCN5YS)
 - or rigid silver-plated (ref. RASYS) copper core - class 1 as per IEC 60228 / DIN VDE 0295.

Characteristics

General

- Continuous operating temperatures:
 - > Silver-plated copper core: -90 °C to +200 °C.
 - > Nickel-plated copper core: -90 °C to +250 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity.
- Excellent resistance to hydrocarbons and fluids.

Electrical

- Rated voltage: 300/500 V.
- Test voltage: 2000 V.

Standard products

- Standard insulation colour: white.



- Flexible nickel-plated (ref. CN5YS) or silver-plated (ref. A5YS) copper core - class 5 as per IEC 60228 / DIN VDE 0295.
- Insulation: Crossed and heat-sealed PTFE tapes.

CN5YS and A5YS

Flexible core • class 5 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.25*	19 x 0.13	89.3
0.5	16 x 0.20	40.1
0.75	24 x 0.20	26.7
1	32 x 0.20	20.0
1.5	30 x 0.25	13.7
2.5	50 x 0.25	8.21
4	56 x 0.30	5.09
6	84 x 0.30	3.39

INSULATED WIRE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.30	1.25	4.3
0.30	1.55	7.1
0.30	1.8	10.6
0.30	1.9	13.2
0.30	2.2	16.6
0.35	2.8	26.7
0.40	3.3	41.6
0.40	3.9	60.5

* Nominal cross-section not described in IEC 60228.

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

omerin
LES CABLES DE L'EXTREME

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® Style 10506

PTFE insulation

UL and cUL approval

-90 °C to +250 °C

Approvals - standards

- Nickel-plated copper complying with the 2% class as per standard ASTM B355.
- UL approval as per standard UL 758 – File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 – File no.: E101965.
- "Horizontal flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.



Applications

- Internal cabling for electrical or electronic appliances.

Options

- Pure nickel core: contact us.
- 27% nickel-plated copper core: contact us.
- Other nominal cross-sections: contact us.
- Other nominal stranding: contact us.
- Other style no. available: style 10487 with PTFE tape + glass tape(s) based insulation.

Characteristics

General

- Continuous operating temperatures: -90 °C to +250 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 600 V.
- Test voltage: 2000 V.

Standard products

- Standard insulation colours: all solid colours.



- 1 • Multistrand nickel-plated copper core.
- 2 • Insulation: PTFE tape(s).

Style 10506

MULTISTRAND CORE

Nominal cross-section AWG	(mm ²)	Nominal stranding*
30	0.05	7 x 0.10
28	0.09	7 x 0.13
26	0.14	7 x 0.16
24	0.22	7 x 0.20
22	0.34	7 x 0.25
-	0.5	7 x 0.30
20	0.6	19 x 0.20
-	0.75	24 x 0.20
18	0.93	19 x 0.25
-	1	32 x 0.20
16	1.34	19 x 0.30
-	1.5	30 x 0.25
14	-	29 x 0.30
-	2.5	50 x 0.25
12	-	46 x 0.30
-	4	56 x 0.30

INSULATED WIRE

Nominal thickness of insulation (mm)	Nominal diameter** (mm)	Approximate linear weight (kg/km)
0.15	0.66	1.1
0.15	0.76	1.6
0.15	0.86	2.1
0.15	0.99	3.0
0.15	1.16	4.4
0.15	1.30	6.1
0.15	1.38	7.0
0.15	1.51	8.7
0.18	1.70	10.9
0.18	1.76	11.7
0.18	1.96	15.1
0.18	2.05	16.5
0.18	2.33	22.3
0.18	2.53	26.5
0.18	2.98	34.9
0.18	3.25	42.1

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* The most common nominal stranding. Some stranding is not available in all types of conductor metals. Other stranding can be produced taking into account the possibilities permitted by standard UL 758 and/or IEC 60228.

** The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® HT

Ignition wires

-90 °C to +260 °C



- 1 • Bare, tin-plated, nickel-plated or silver-plated copper core.
- 2 • Insulation: Fluorinated polymer.

Applications

- Ignition circuit, creation of an electric arc for piezo-electric system of household electric appliances, burners, etc.

Options

- Pure nickel core: contact us.
- Outer electrical shielding:
 - > Tin-plated copper braid: contact us.
- Other nominal cross-sections: contact us.
 - Other nominal stranding: contact us.
 - Other colours: contact us.

Characteristics General

- Continuous operating temperatures:
 - > ETFE insulation: -90 °C to +155 °C.
 - > FEP insulation: -90 °C to +205 °C.
 - > MFA insulation: -90 °C to +250 °C.
 - > PFA insulation: -90 °C to +260 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Pulse voltage: from 12 to 30 kV.

Standard products

- Main products: see table below.
- Standard insulation colours: translucent or white.

Core	Insulation ETFE	Insulation FEP	Insulation MFA	Insulation PFA
In bare copper	ETFE-HT	FEP-HT	MFA-HT	PFA-HT
In tin-plated copper	EETFE-HT	EFEP-HT	EMFA-HT	EPFA-HT
In silver-plated copper	AETFE-HT	AFEP-HT	AMFA-HT	APFA-HT
In nickel-plated copper	CNETFE-HT	CNFEF-HT	CNMFA-HT	CNPFA-HT

INSULATED WIRE - Voltage*

CONDUCTING CORE			12 KV		15 KV		20 KV		25 KV		30 KV	
Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km) (tin-plated copper core)	Nominal diameter (mm)	Approximate linear weight (kg/km)	Nominal diameter (mm)	Approximate linear weight (kg/km)	Nominal diameter (mm)	Approximate linear weight (kg/km)	Nominal diameter (mm)	Approximate linear weight (kg/km)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.22	7 x 0.20	92.5	1.4	4.7	1.5	5.2	1.7	6.3	1.8	6.8	2.0	8.1
0.34	7 x 0.25	59.2	1.6	6.5	1.7	7.0	1.8	7.6	2.0	8.9	2.2	10.3
0.5	16 x 0.20	40.1	1.7	8.1	1.8	8.7	1.9	9.3	2.1	10.7	2.3	12.2
0.6	19 x 0.20	33.7	1.8	9.3	1.9	9.9	2.0	10.6	2.2	12.0	2.4	13.6
0.75	24 x 0.20	26.7	1.9	10.9	2.0	11.6	2.1	12.3	2.3	13.8	2.5	15.4
0.93	19 x 0.25	21.6	2.0	12.8	2.1	13.5	2.3	14.9	2.4	15.7	2.6	17.4
1	32 x 0.20	20.0	2.1	13.9	2.2	14.6	2.3	15.4	2.5	17.0	2.7	18.8
1.34	19 x 0.30	15.0	2.3	17.6	2.4	18.4	2.5	19.2	2.7	21.0	2.8	21.9
1.5	30 x 0.25	13.7	2.4	19.2	2.4	19.2	2.6	20.9	2.7	21.8	2.9	23.6
2.5	50 x 0.25	8.21	2.8	29.0	2.9	29.9	3.0	30.9	3.2	33.0	3.3	34.1

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* Pulse voltage.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® HT

Ignition wires

UL and cUL approval



Approvals - standards

- UL approval as per standard UL 758 – File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 – File no.: E101965.
- "Horizontal flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.

Applications

- Ignition circuit, creation of an electric arc for piezo-electric system of household electric appliances, burners, etc.

Options

- Pure nickel core: contact us.
- 27% nickel-plated copper core: contact us.
- Other nominal cross-sections: contact us.

Characteristics

General


- Continuous operating temperatures: -90 °C to +250 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Pulse voltage: as per style no. except style 1813.

Standard products

- All colours including translucent.
- Stranding of conducting cores: contact us.



- 1 • Bare, tin-plated, nickel-plated or silver-plated copper core.
- 2 • Insulation: Fluorinated polymer.

Style no.	10185-E150		1911-F150		1813		10185-E200		1911-F250	
Approval	150 °C – 10 KV AC** (cUL 600 V)		150 °C – 20 KV DC** (cUL 1000 V)		200 °C – 3000 V (cUL 1000 V)		200 °C – 10 KV AC** (cUL 150°C-600 V)		250 °C – 20 KV DC**	
Nominal cross-section	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)
AWG (mm²)										
30 (0.05)	-	-	-	-	0.64	1.6	-	-	-	-
28 (0.09)	-	-	-	-	0.64	1.7	-	-	-	-
26 (0.13)	-	-	-	-	0.64	1.8	-	-	-	-
24 (0.22)	0.36	1.4	0.48	1.6	0.64	1.9	0.36	1.4	0.61	1.8
22 (0.34)	0.36	1.5	0.48	1.75	0.64	2.05	0.36	1.5	0.61	1.95
- (0.5)	0.36	1.65	0.48	1.9	0.64	2.2	0.36	1.65	0.61	2.15
20 (0.6)	0.36	1.7	0.48	2.0	0.64	2.3	0.36	1.7	0.61	2.15
- (0.75)	0.36	1.85	0.48	2.1	0.64	2.4	0.36	1.85	0.61	2.35
18 (0.93)	0.36	2.0	0.48	2.2	0.64	2.55	0.36	2.0	0.61	2.5
- (1)	0.36	2.05	0.48	2.25	0.64	2.6	0.36	2.05	0.61	2.55
16 (1.34)	0.36	2.2	0.48	2.5	0.64	2.8	0.36	2.2	0.61	2.7
- (1.5)	0.36	2.3	0.48	2.55	0.64	2.9	0.36	2.3	0.61	2.8
14 (-)	0.36	2.6	0.48	2.9	0.64	3.15	0.36	2.6	0.61	3.0
- (2.5)	0.36	2.8	0.48	3.0	0.64	3.35	0.36	2.8	0.61	3.3
12 (-)	0.36	3.1	0.48	3.35	0.64	3.65	0.36	3.1	0.61	3.6
- (4)	0.36	3.4	0.48	3.6	0.64	3.9	0.36	3.4	0.61	3.85
10 (-)	0.36	3.8	0.48	4.0	0.64	4.3	0.36	3.8	0.61	4.25
- (6)	0.36	3.9	0.48	4.2	0.64	4.5	0.36	3.9	0.61	4.4
Conducting metal	BCDEFG		BCDEFG		B*CDEFG		B*CDEF*G		CEG	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27%

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* The diameter is provided for information purposes as it may vary depending on the stranding of the core.
Only the average thickness of insulation should be taken into account.
** Pulse voltage.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® M6-E6**-90 °C to +205 °C**

- 1 • Flexible tin-plated copper core – class 5 as per IEC 60228.
- 2 • Insulation: Fluorinated polymer FEP.
- 3 • Outer sheath: Fluorinated polymer FEP.

Applications

- Cabling in household electrical appliances, electronics.
 - Cabling in hot or cold environments (cryogenics).
 - Cabling in aggressive environments (humidity, chemicals, etc.).
 - Cabling requiring compact size and excellent mechanical strength.
- Cabling of thermoresistant detectors type PT 100.

Options

- Bare copper core: ref. M6-6.
- Silver-plated copper core: ref. M6-A6.
- Nickel-plated copper core: ref. M6-CN6.
- Pure nickel core (not described in IEC 60228): ref. M6-N6.
 - PFA fluorinated polymer insulation and sheathing for continuous operating temperatures up to +260°C: ref. M5-E5.
 - ETFE fluorinated polymer insulation and sheathing for continuous operating temperatures up to +155 °C: ref. M7-E7.
 - Other nominal metric or American cross-sections: contact us.
- Other numbers of conductors: contact us.
 - Other nominal stranding: contact us.
 - Other colours: contact us.
- Other options and/or combinations of the options outlined above: contact us.

Characteristics**General**

- Continuous operating temperatures: -90°C to +205 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 300/500 V.
- Test voltage: 2000 V.

Standard products

- Standard conductor colours: all solid colours including yellow/green.
- Standard outer sheath colours: grey, white or black.

For this product, please contact:

OMERIN division principale ✓

Zone Industrielle - F 63600 Ambert

Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10

omerin@omerin.com

omerin
LES CABLES DE L'EXTREME

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.

For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Flexible core • class 5 as per IEC 60228

INSULATED CONDUCTORS

SHEATHED CABLE

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)	Nominal thickness of insulation (mm)	Nominal diameter (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
2 x 0.5	16 x 0.20	40.1	0.20	1.3	3.1	17.0
3 x 0.5	16 x 0.20	40.1	0.20	1.3	3.3	23.3
4 x 0.5	16 x 0.20	40.1	0.20	1.3	3.6	29.6
5 x 0.5	16 x 0.20	40.1	0.20	1.3	4.1	38.0
7 x 0.5	16 x 0.20	40.1	0.20	1.3	4.5	51.1
2 x 0.75	24 x 0.20	26.7	0.20	1.45	3.4	22.1
3 x 0.75	24 x 0.20	26.7	0.20	1.45	3.6	30.5
4 x 0.75	24 x 0.20	26.7	0.20	1.45	4.0	39.9
5 x 0.75	24 x 0.20	26.7	0.20	1.45	4.6	51.8
7 x 0.75	24 x 0.20	26.7	0.20	1.45	5.0	69.0
2 x 1	32 x 0.20	20.0	0.20	1.7	3.9	28.8
3 x 1	32 x 0.20	20.0	0.20	1.7	4.2	41.0
4 x 1	32 x 0.20	20.0	0.20	1.7	4.6	52.7
5 x 1	32 x 0.20	20.0	0.20	1.7	5.3	68.5
7 x 1	32 x 0.20	20.0	0.20	1.7	5.7	90.2
2 x 1.5	30 x 0.25	13.7	0.20	1.95	4.4	38.7
3 x 1.5	30 x 0.25	13.7	0.20	1.95	4.7	54.9
4 x 1.5	30 x 0.25	13.7	0.20	1.95	5.3	73.6
5 x 1.5	30 x 0.25	13.7	0.20	1.95	5.9	91.3
7 x 1.5	30 x 0.25	13.7	0.20	1.95	6.6	127
2 x 2.5	50 x 0.25	8.21	0.20	2.5	5.6	63.3
3 x 2.5	50 x 0.25	8.21	0.20	2.5	6.2	94.5
4 x 2.5	50 x 0.25	8.21	0.20	2.5	6.8	122
5 x 2.5	50 x 0.25	8.21	0.20	2.5	7.6	152
7 x 2.5	50 x 0.25	8.21	0.20	2.5	8.4	208
2 x 4	56 x 0.30	5.09	0.25	3.1	7.2	102
3 x 4	56 x 0.30	5.09	0.25	3.1	7.9	149
4 x 4	56 x 0.30	5.09	0.25	3.1	8.7	192
5 x 4	56 x 0.30	5.09	0.25	3.1	9.6	235
7 x 4	56 x 0.30	5.09	0.25	3.1	10.9	333
2 x 6	84 x 0.30	3.39	0.35	3.9	9.0	162
3 x 6	84 x 0.30	3.39	0.35	3.9	9.6	228
4 x 6	84 x 0.30	3.39	0.35	3.9	10.8	303
5 x 6	84 x 0.30	3.39	0.35	3.9	12.1	380
7 x 6	84 x 0.30	3.39	0.35	3.9	13.7	532

For this product, please contact:

OMERIN division principale 
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com


www.omerin.com

omerin
 LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
 For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® M6BE-E6

-90 °C to +205 °C



- 1 • Flexible tin-plated copper core – class 5 as per IEC 60228.
- 2 • Insulation: Fluorinated polymer FEP.
- 3 • Electrical shielding: Tin-plated copper braid.
- 4 • Outer sheath: Fluorinated polymer FEP.

Applications

- Cabling for electrical heating appliances.
 - Use in the medical field as cabling for sterilisable surgical instruments.
 - All power cords requiring resistance to alternate bendings.
- Cabling of thermoresistant detectors type PT 100.

Options

- Bare copper core: contact us.
- Silver-plated copper core: contact us.
- Nickel-plated copper core: contact us.
- Pure nickel core (not described in IEC 60228): contact us.
- Electrical shielding made of an aluminium tape + continuity wire (ref. M6BAL-E6): contact us.
 - PFA fluorinated polymer insulation and sheathing for continuous operating temperatures up to +260°C: ref. M5BE-E5.
 - ETFE fluorinated polymer insulation and sheathing for continuous operating temperatures up to +155 °C: ref. M7BE-E7.
- Other nominal metric or American cross-sections: contact us.
- Other numbers of conductors: contact us.
 - Other nominal stranding: contact us.
 - Other colours: contact us.
- Other options and/or combinations of the options outlined above: contact us.

Characteristics

General

- Continuous operating temperatures: -90 °C to +205 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical

- Rated voltage: 300/500 V.
- Test voltage: 2000 V.

Standard products

- Standard conductor colours: all solid colours including yellow/green.
- Standard outer sheath colours: grey, white or black.

For this product, please contact:

OMERIN division principale ✓

Zone Industrielle - F 63600 Ambert

Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10

omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Flexible core • class 5 as per IEC 60228

INSULATED CONDUCTORS

SHEATHED CABLE

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)	Nominal thickness of insulation (mm)	Nominal diameter (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
2 x 0.5	16 x 0.20	40.1	0.20	1.3	3.6	30.0
3 x 0.5	16 x 0.20	40.1	0.20	1.3	3.8	37.3
4 x 0.5	16 x 0.20	40.1	0.20	1.3	4.1	45.0
5 x 0.5	16 x 0.20	40.1	0.20	1.3	4.6	55.2
7 x 0.5	16 x 0.20	40.1	0.20	1.3	4.9	68.3
2 x 0.75	24 x 0.20	26.7	0.20	1.45	3.8	35.2
3 x 0.75	24 x 0.20	26.7	0.20	1.45	4.0	44.4
4 x 0.75	24 x 0.20	26.7	0.20	1.45	4.5	56.9
5 x 0.75	24 x 0.20	26.7	0.20	1.45	5.0	69.1
7 x 0.75	24 x 0.20	26.7	0.20	1.45	5.6	95.6
2 x 1	32 x 0.20	20.0	0.20	1.7	4.6	48.4
3 x 1	32 x 0.20	20.0	0.20	1.7	4.8	60.4
4 x 1	32 x 0.20	20.0	0.20	1.7	5.1	72.3
5 x 1	32 x 0.20	20.0	0.20	1.7	5.6	90.7
7 x 1	32 x 0.20	20.0	0.20	1.7	6.4	123
2 x 1.5	30 x 0.25	13.7	0.20	1.95	4.8	55.8
3 x 1.5	30 x 0.25	13.7	0.20	1.95	5.4	78.5
4 x 1.5	30 x 0.25	13.7	0.20	1.95	6.2	108
5 x 1.5	30 x 0.25	13.7	0.20	1.95	6.8	130
7 x 1.5	30 x 0.25	13.7	0.20	1.95	7.6	172
2 x 2.5	50 x 0.25	8.21	0.20	2.5	6.4	97.6
3 x 2.5	50 x 0.25	8.21	0.20	2.5	6.8	127
4 x 2.5	50 x 0.25	8.21	0.20	2.5	7.5	160
5 x 2.5	50 x 0.25	8.21	0.20	2.5	8.5	201
7 x 2.5	50 x 0.25	8.21	0.20	2.5	9.2	259
2 x 4	56 x 0.30	5.09	0.25	3.1	7.7	138
3 x 4	56 x 0.30	5.09	0.25	3.1	8.4	187
4 x 4	56 x 0.30	5.09	0.25	3.1	9.3	238
5 x 4	56 x 0.30	5.09	0.25	3.1	10.1	282
7 x 4	56 x 0.30	5.09	0.25	3.1	11.5	394
2 x 6	84 x 0.30	3.39	0.35	3.9	9.5	205
3 x 6	84 x 0.30	3.39	0.35	3.9	10.1	275
4 x 6	84 x 0.30	3.39	0.35	3.9	11.5	363
5 x 6	84 x 0.30	3.39	0.35	3.9	13.1	466
7 x 6	84 x 0.30	3.39	0.35	3.9	14.3	608

For this product, please contact:

OMERIN division principale 
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com


www.omerin.com

omerin
 LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
 For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® KU 03, KU 04 KU 05 and KU 06

-55 °C to +150 °C



Approvals - standards

- Inspired from NF C 93-524 standard.

Applications

- Wires used in aeronautical, electronic and all instrumentation applications requiring high resistance to high temperatures and to chemical influences.

Options

- Other colours: contact us.

Characteristics

General

- Continuous operating temperatures: -55 °C to +150 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
- Excellent mechanical strength.

Electrical (as per UTE C 93-524)

- Rated voltage: 600 Vac – 850 Vdc.
- Test voltage: KU 03 and KU 04: 3400 Vac.
KU 05 and KU 06: 1500 Vac.

Standard products

- Standard conductor colours of the pair: white and blue.
- Standard conductor colours of the triple: white, blue and orange.
- Standard outer sheath colour: white.

CONDUCTORS (TYPE KU 01)

Nominal cross-section AWG (mm²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)	Nominal diameter (mm)
30	0.05 7 x 0.10	365.4	0.63
28	0.09 7 x 0.13	208.0	0.69
26	0.15 19 x 0.10	128.7	0.81
24	0.25 19 x 0.13	76.6	0.91
22	0.38 19 x 0.16	50.3	1.10
20	0.60 19 x 0.20	32.1	1.52
18	0.93 19 x 0.25	20.6	1.80
16	1.34 19 x 0.30	14.3	2.00
14	1.82 37 x 0.25	10.6	2.36
12	3.00 37 x 0.32	6.5	2.89

KU 03	
Nominal diameter (mm)	Approximate linear weight (kg/km)
1.26	1.8
1.38	2.6
1.62	3.8
1.82	5.7
2.20	8.5
3.04	13.9
3.60	21.2
4.00	29.1
4.72	39.4
5.78	72.9

KU 04	
Nominal diameter (mm)	Approximate linear weight (kg/km)
1.36	2.7
1.48	3.9
1.74	5.8
1.96	8.5
2.37	12.7
3.27	20.9
3.87	31.8
4.30	43.6
5.08	59.1
6.22	109

KU 05	
Nominal diameter (mm)	Approximate linear weight (kg/km)
2.10	8.7
2.22	9.8
2.47	11.8
2.76	15.0
3.14	21.0
3.97	30.4
4.54	42.5
4.94	52.4
5.72	67.7
6.78	114

KU 06	
Nominal diameter (mm)	Approximate linear weight (kg/km)
2.31	10.2
2.43	11.6
2.68	13.9
2.89	18.5
3.30	25.3
4.22	38.4
4.82	51.3
5.24	65.9
6.09	90.9
7.24	146

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com


www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

SILIFLON® 150 °C

Fluoropolymer insulation Fluoropolymer sheathing UL and cUL approval



- 1 • UL and cUL approved conductors with fluoropolymer insulation.
- 2 • Outer sheath: Fluorinated polymer.

Characteristics General

- Continuous operating temperatures: -90 °C to +150 °C.
- Excellent resistance to aggressive chemical environments.
- Excellent resistance to humidity and UV.
 - Excellent mechanical strength.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- Single conductors: UL and cUL approved conductors with fluoropolymer insulation (≥ 150 °C).
- Standard outer sheath colours: white, black or grey.
 - Stranding of conducting cores: contact us.

Approvals - standards

- UL and cUL approval as per standard UL 758 and C22.2 No. 210 – File no.: E101965.
- “Horizontal flame test” or “Cable flame test” as per UL approval.
- “FT1 flame rating” as per cUL approval.

Applications

- Internal cabling for electrical heating appliances.
- External connections for electrical heating appliances.

Options

- Electrical shielding: Tin-plated copper braid, or aluminium tape + continuity wire.
 - Other outer sheath colours: contact us.
 - Other nominal cross-sections: contact us.
- Conductors with a silicone insulation : contact us.

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring
- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections

* The diameter is provided for information only, as it may vary depending on the stranding of the core.
Only the average thickness of insulation or the sheathing should be taken into account.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

Style no. Insulation Approval	20221-E150 ETFE "Thin-wall"		20905-E150 ETFE "Thin-wall"		20222-E150 ETFE "Thin-wall"			
	150 °C – 300 V		150 °C – 300 V		150 °C – 600 V			
	AWM II A/B (Wall 0.25 mm)		AWM II A/B (Wall 0.51 mm)		AWM II A/B (Wall 0.38 mm)			
No. of cond.	AWG	Nominal cross-section (mm²)	Nominal diameter of the cond.* (mm)	Nominal diameter of the cable* (mm)	Nominal diameter of the cond.* (mm)	Nominal diameter of the cable* (mm)	Nominal diameter of the cond.* (mm)	Nominal diameter of the cable* (mm)
2	26	0.13	0.75	2.0	0.75	2.5	1.05	2.9
3	26	0.13	0.75	2.1	0.75	2.6	1.05	3.0
4	26	0.13	0.75	2.3	0.75	2.8	1.05	3.3
5	26	0.13	0.75	2.6	0.75	3.0	1.05	3.6
7	26	0.13	0.75	2.9	0.75	3.3	1.05	4.0
2	24	0.22	0.9	2.3	0.9	2.8	1.15	3.1
3	24	0.22	0.9	2.4	0.9	3.0	1.15	3.2
4	24	0.22	0.9	2.8	0.9	3.2	1.15	3.5
5	24	0.22	0.9	3.0	0.9	3.5	1.15	3.9
7	24	0.22	0.9	3.3	0.9	3.7	1.15	4.3
2	22	0.34	1.05	2.7	1.05	3.1	1.3	3.4
3	22	0.34	1.05	2.9	1.05	3.3	1.3	3.6
4	22	0.34	1.05	3.1	1.05	3.6	1.3	3.9
5	22	0.34	1.05	3.4	1.05	3.9	1.3	4.3
7	22	0.34	1.05	4.0	1.05	4.2	1.3	4.7
2	-	0.5	1.25	3.1	1.25	3.5	1.4	3.6
3	-	0.5	1.25	3.3	1.25	3.7	1.4	3.8
4	-	0.5	1.25	3.8	1.25	4.0	1.4	4.2
5	-	0.5	1.25	4.2	1.25	4.4	1.4	4.6
7	-	0.5	1.25	4.6	1.25	4.8	1.4	5.0
2	20	0.6	1.3	3.2	1.3	3.6	1.5	3.8
3	20	0.6	1.3	3.4	1.3	3.8	1.5	4.0
4	20	0.6	1.3	3.9	1.3	4.2	1.5	4.4
5	20	0.6	1.3	4.3	1.3	4.5	1.5	4.9
7	20	0.6	1.3	4.7	1.3	4.9	1.5	5.3
2	-	0.75	1.4	3.4	1.4	3.8	1.55	3.9
3	-	0.75	1.4	3.8	1.4	4.0	1.55	4.1
4	-	0.75	1.4	4.2	1.4	4.4	1.55	4.5
5	-	0.75	1.4	4.6	1.4	4.8	1.55	5.0
7	-	0.75	1.4	5.0	1.4	5.2	1.55	5.5
2	18	0.93	1.55	3.9	1.55	4.1	1.8	4.4
3	18	0.93	1.55	4.1	1.55	4.4	1.8	4.7
4	18	0.93	1.55	4.5	1.55	4.8	1.8	5.1
5	18	0.93	1.55	5.0	1.55	5.2	1.8	5.7
7	18	0.93	1.55	5.5	1.55	5.7	1.8	6.4
2	-	1	1.65	4.1	1.65	4.3	1.8	4.4
3	-	1	1.65	4.4	1.65	4.6	1.8	4.7
4	-	1	1.65	4.8	1.65	5.0	1.8	5.1
5	-	1	1.65	5.3	1.65	5.5	1.8	5.7
7	-	1	1.65	5.8	1.65	6.0	1.8	6.4
2	16	1.34	1.9	4.6	1.9	4.8	2.0	4.8
3	16	1.34	1.9	4.9	1.9	5.1	2.0	5.1
4	16	1.34	1.9	5.4	1.9	5.6	2.0	5.6
5	16	1.34	1.9	6.1	1.9	6.2	2.0	6.4
7	16	1.34	1.9	6.7	1.9	6.7	2.0	7.0
2	-	1.5	1.9	4.6	1.9	4.8	2.0	4.8
3	-	1.5	1.9	4.9	1.9	5.1	2.0	5.1
4	-	1.5	1.9	5.4	1.9	5.6	2.0	5.6
5	-	1.5	1.9	6.1	1.9	6.2	2.0	6.4
7	-	1.5	1.9	6.7	1.9	6.7	2.0	7.0
2	14	-	2.25	5.3	2.25	5.5	2.4	5.6
3	14	-	2.25	5.7	2.25	5.9	2.4	6.2
4	14	-	2.25	6.4	2.25	6.4	2.4	6.8
5	14	-	2.25	7.1	2.25	7.1	2.4	7.5
7	14	-	2.25	7.8	2.25	7.8	2.4	8.4

Conducting metal

BCDEFG

BCDEFG

BCDEFG

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.



SILIFLON® 200 °C

Fluoropolymer insulation
Fluoropolymer sheathing
UL and cUL approval



- 1 • UL and cUL approved conductors with fluoropolymer insulation.
- 2 • Outer sheath: Fluorinated polymer.

Characteristics General

- Continuous operating temperatures: -90 °C to +200 °C.
- Excellent resistance to aggressive chemical environments.
 - Excellent resistance to humidity and UV.
 - Excellent mechanical strength.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- Single conductors: UL and cUL approved conductors with fluoropolymer insulation (200 °C).
- Outer sheath colours: white, black or grey.
- Stranding of conducting cores: contact us.

Approvals - standards

- UL and cUL approval as per standard UL 758 and C22.2 No. 210 – File no.: E101965.
- "Horizontal flame test" or "Cable flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.

Applications

- Internal cabling for electrical heating appliances.
- External connections for electrical heating appliances.

Options

- Electrical shielding: Tin-plated copper braid, or aluminium tape + continuity wire.
- Other outer sheath colours: contact us.
- Other nominal cross-sections: contact us.
- Conductors with a silicone insulation : contact us.
- Other style nos. available: styles no. 2895, 20262, 20920.

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core.
Only the average thickness of insulation or the sheathing should be taken into account.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com



www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

No. of cond.	AWG	Nominal cross-section (mm ²)	20711-F200 ETFE "Thin-wall"		20711-F200 FEP		2749-F200 ETFE "Thin-wall"	
			200 °C - 300 V AWM I A/B (Wall 0.25 mm)		200 °C - 300 V AWM I A/B (Wall 0.25 mm)		200 °C - 300 V AWM I A/B (Wall 0.51 mm)	
			Nominal diameter of the cond.* (mm)	Nominal diameter of the cable* (mm)	Nominal diameter of the cond.* (mm)	Nominal diameter of the cable* (mm)	Nominal diameter of the cond.* (mm)	Nominal diameter of the cable* (mm)
2	26	0.13	0.8	2.1	1.0	2.5	0.8	2.6
3	26	0.13	0.8	2.2	1.0	2.8	0.8	2.7
4	26	0.13	0.8	2.4	1.0	3.0	0.8	2.9
5	26	0.13	0.8	2.7	1.0	3.3	0.8	3.1
7	26	0.13	0.8	3.0	1.0	3.6	0.8	3.4
2	24	0.22	0.9	2.3	1.1	2.8	0.9	2.8
3	24	0.22	0.9	2.4	1.1	3.0	0.9	2.9
4	24	0.22	0.9	2.7	1.1	3.3	0.9	3.1
5	24	0.22	0.9	3.0	1.1	3.6	0.9	3.4
7	24	0.22	0.9	3.3	1.1	4.1	0.9	3.7
2	22	0.34	1.05	2.7	1.25	3.1	1.05	3.1
3	22	0.34	1.05	2.8	1.25	3.3	1.05	3.2
4	22	0.34	1.05	3.1	1.25	3.8	1.05	3.5
5	22	0.34	1.05	3.4	1.25	4.2	1.05	3.8
7	22	0.34	1.05	3.9	1.25	4.6	1.05	4.1
2	-	0.5	1.25	3.1	1.4	3.4	1.25	3.5
3	-	0.5	1.25	3.3	1.4	3.8	1.25	3.7
4	-	0.5	1.25	3.8	1.4	4.2	1.25	4.0
5	-	0.5	1.25	4.1	1.4	4.6	1.25	4.3
7	-	0.5	1.25	4.5	1.4	5.0	1.25	4.7
2	20	0.6	1.3	3.2	1.5	3.6	1.3	3.6
3	20	0.6	1.3	3.4	1.5	4.0	1.3	3.8
4	20	0.6	1.3	3.9	1.5	4.4	1.3	4.1
5	20	0.6	1.3	4.3	1.5	4.9	1.3	4.5
7	20	0.6	1.3	4.7	1.5	5.3	1.3	4.9
2	-	0.75	1.4	3.4	1.55	3.9	1.4	3.8
3	-	0.75	1.4	3.8	1.55	4.1	1.4	4.0
4	-	0.75	1.4	4.1	1.55	4.5	1.4	4.3
5	-	0.75	1.4	4.5	1.55	5.0	1.4	4.8
7	-	0.75	1.4	5.0	1.55	5.5	1.4	5.2
2	18	0.93	1.55	3.9	1.7	4.2	1.55	4.1
3	18	0.93	1.55	4.1	1.7	4.5	1.55	4.3
4	18	0.93	1.55	4.5	1.7	4.9	1.55	4.7
5	18	0.93	1.55	4.9	1.7	5.4	1.55	5.2
7	18	0.93	1.55	5.4	1.7	6.1	1.55	5.6
2	-	1	1.65	4.1	1.8	4.4	1.65	4.3
3	-	1	1.65	4.3	1.8	4.7	1.65	4.5
4	-	1	1.65	4.7	1.8	5.1	1.65	4.9
5	-	1	1.65	5.2	1.8	5.7	1.65	5.4
7	-	1	1.65	5.7	1.8	6.4	1.65	5.9
2	16	1.34	1.9	4.6	2.0	4.8	1.9	4.8
3	16	1.34	1.9	4.9	2.0	5.1	1.9	5.1
4	16	1.34	1.9	5.3	2.0	5.6	1.9	5.5
5	16	1.34	1.9	6.1	2.0	6.4	1.9	6.1
7	16	1.34	1.9	6.7	2.0	7.0	1.9	6.7
2	-	1.5	1.9	4.6	2.0	4.8	1.9	4.8
3	-	1.5	1.9	4.9	2.0	5.1	1.9	5.1
4	-	1.5	1.9	5.3	2.0	5.6	1.9	5.5
5	-	1.5	1.9	6.1	2.0	6.4	1.9	6.1
7	-	1.5	1.9	6.7	2.0	7.0	1.9	6.7
2	14	-	2.25	5.3	2.4	5.6	2.25	5.5
3	14	-	2.25	5.6	2.4	6.2	2.25	5.8
4	14	-	2.25	6.4	2.4	6.8	2.25	6.4
5	14	-	2.25	7.0	2.4	7.5	2.25	7.0
7	14	-	2.25	7.7	2.4	8.4	2.25	7.7

Conducting metal

B*CDEF*G

B*CDEG

B*CDEF*G

Style no. Insulation			2749-F200 FEP		20710-F200 ETFE "Thin-wall"		20710-F200 FEP		2750-F200 ETFE "Thin-wall"		2750-F200 FEP	
Approval			200 °C - 300 V AWM I A/B (Wall 0.25 mm)		200 °C - 600 V AWM I A/B (Wall 0.30 mm)		200 °C - 600 V AWM I A/B (Wall 0.30 mm)		200 °C - 600 V AWM I A/B (Wall 0.51 mm)		200 °C - 600 V AWM I A/B (Wall 0.51 mm)	
No. of cond.	Nominal cross-section		Nominal diameter of the cond.* of the cable* (mm)	Nominal diameter of the cable* (mm)	Nominal diameter of the cond.* of the cable* (mm)	Nominal diameter of the cable* (mm)	Nominal diameter of the cond.* of the cable* (mm)	Nominal diameter of the cable* (mm)	Nominal diameter of the cond.* of the cable* (mm)	Nominal diameter of the cable* (mm)	Nominal diameter of the cond.* of the cable* (mm)	Nominal diameter of the cable* (mm)
	AWG	(mm ²)										
2	26	0.13	1.0	3.0	1.0	2.6	1.2	3.0	1.0	3.0	1.2	3.4
3	26	0.13	1.0	3.2	1.0	2.7	1.2	3.2	1.0	3.1	1.2	3.6
4	26	0.13	1.0	3.4	1.0	3.0	1.2	3.5	1.0	3.4	1.2	3.9
5	26	0.13	1.0	3.7	1.0	3.3	1.2	4.0	1.0	3.7	1.2	4.3
7	26	0.13	1.0	4.0	1.0	3.6	1.2	4.4	1.0	4.0	1.2	4.6
2	24	0.22	1.1	3.2	1.1	2.8	1.35	3.3	1.1	3.2	1.35	3.7
3	24	0.22	1.1	3.4	1.1	2.9	1.35	3.5	1.1	3.3	1.35	3.9
4	24	0.22	1.1	3.7	1.1	3.2	1.35	4.1	1.1	3.6	1.35	4.3
5	24	0.22	1.1	4.0	1.1	3.5	1.35	4.4	1.1	3.9	1.35	4.7
7	24	0.22	1.1	4.3	1.1	4.1	1.35	4.9	1.1	4.3	1.35	5.1
2	22	0.34	1.25	3.5	1.25	3.1	1.45	3.5	1.25	3.5	1.45	3.9
3	22	0.34	1.25	3.7	1.25	3.3	1.45	3.9	1.25	3.7	1.45	4.2
4	22	0.34	1.25	4.0	1.25	3.8	1.45	4.3	1.25	4.0	1.45	4.5
5	22	0.34	1.25	4.4	1.25	4.1	1.45	4.7	1.25	4.3	1.45	4.9
7	22	0.34	1.25	4.8	1.25	4.5	1.45	5.2	1.25	4.7	1.45	5.4
2	-	0.5	1.4	3.8	1.4	3.4	1.65	4.1	1.4	3.8	1.65	4.3
3	-	0.5	1.4	4.0	1.4	3.8	1.65	4.4	1.4	4.0	1.65	4.6
4	-	0.5	1.4	4.4	1.4	4.1	1.65	4.8	1.4	4.3	1.65	5.0
5	-	0.5	1.4	4.8	1.4	4.5	1.65	5.3	1.4	4.8	1.65	5.5
7	-	0.5	1.4	5.2	1.4	5.0	1.65	5.8	1.4	5.2	1.65	6.0
2	20	0.6	1.5	4.0	1.5	3.6	1.7	4.2	1.5	4.0	1.7	4.4
3	20	0.6	1.5	4.3	1.5	4.0	1.7	4.5	1.5	4.2	1.7	4.7
4	20	0.6	1.5	4.6	1.5	4.4	1.7	4.9	1.5	4.6	1.7	5.1
5	20	0.6	1.5	5.1	1.5	4.8	1.7	5.4	1.5	5.0	1.7	5.6
7	20	0.6	1.5	5.5	1.5	5.3	1.7	6.1	1.5	5.5	1.7	6.1
2	-	0.75	1.55	4.1	1.55	3.9	1.8	4.4	1.55	4.1	1.8	4.6
3	-	0.75	1.55	4.4	1.55	4.1	1.8	4.7	1.55	4.3	1.8	4.9
4	-	0.75	1.55	4.8	1.55	4.5	1.8	5.1	1.55	4.7	1.8	5.4
5	-	0.75	1.55	5.2	1.55	4.9	1.8	5.7	1.55	5.2	1.8	5.9
7	-	0.75	1.55	5.7	1.55	5.4	1.8	6.4	1.55	5.6	1.8	6.4
2	18	0.93	1.7	4.4	1.8	4.4	2.0	4.8	1.8	4.6	2.0	5.0
3	18	0.93	1.7	4.7	1.8	4.6	2.0	5.1	1.8	4.9	2.0	5.3
4	18	0.93	1.7	5.1	1.8	5.1	2.0	5.6	1.8	5.3	2.0	5.8
5	18	0.93	1.7	5.6	1.8	5.6	2.0	6.4	1.8	5.8	2.0	6.4
7	18	0.93	1.7	6.1	1.8	6.4	2.0	7.0	1.8	6.4	2.0	7.0
2	-	1	1.8	4.6	1.8	4.4	2.0	4.8	1.8	4.6	2.0	5.0
3	-	1	1.8	4.9	1.8	4.6	2.0	5.1	1.8	4.9	2.0	5.3
4	-	1	1.8	5.4	1.8	5.1	2.0	5.6	1.8	5.3	2.0	5.8
5	-	1	1.8	5.9	1.8	5.6	2.0	6.4	1.8	5.8	2.0	6.4
7	-	1	1.8	6.4	1.8	6.4	2.0	7.0	1.8	6.4	2.0	7.0
2	16	1.34	2.0	5.0	2.0	4.8	2.2	5.2	2.0	5.0	2.2	5.4
3	16	1.34	2.0	5.3	2.0	5.1	2.2	5.6	2.0	5.3	2.2	5.8
4	16	1.34	2.0	5.8	2.0	5.6	2.2	6.3	2.0	5.8	2.2	6.3
5	16	1.34	2.0	6.4	2.0	6.4	2.2	6.9	2.0	6.4	2.2	7.0
7	16	1.34	2.0	7.0	2.0	7.0	2.2	7.6	2.0	7.0	2.2	7.6
2	-	1.5	2.0	5.0	2.0	4.8	2.3	5.4	2.0	5.0	2.3	5.6
3	-	1.5	2.0	5.3	2.0	5.1	2.3	5.8	2.0	5.3	2.3	6.0
4	-	1.5	2.0	5.8	2.0	5.6	2.3	6.5	2.0	5.8	2.3	6.6
5	-	1.5	2.0	6.4	2.0	6.4	2.3	7.2	2.0	6.4	2.3	7.2
7	-	1.5	2.0	7.0	2.0	7.0	2.3	7.9	2.0	7.0	2.3	7.9
2	14	-	2.4	5.8	2.4	5.6	2.6	6.2	2.4	5.8	2.6	6.2
3	14	-	2.4	6.2	2.4	6.1	2.6	6.6	2.4	6.2	2.6	6.6
4	14	-	2.4	6.8	2.4	6.7	2.6	7.3	2.4	6.8	2.6	7.3
5	14	-	2.4	7.5	2.4	7.4	2.6	8.2	2.4	7.5	2.6	8.2
7	14	-	2.4	8.4	2.4	8.4	2.6	9.0	2.4	8.4	2.6	9.0

Conducting metal


B*CDEG

B*CDEF*G










B*CDEF*G

B*CDEF*G

B*CDEF*G



THERMOPLASTIC INSULATED WIRES AND CABLES

FT No.	PRODUCT REFERENCE	APPROVAL	PAGE
2201	PLASTHERM Y2 and EY2		48
2202	PLASTHERM 80 °C - PVC insulation		50
2203	PLASTHERM 105 °C - PVC insulation		52
2204	PLASTHERM Style 1015-HAR		54
2205	PLASTHERM Style 20199, 2-conductor flat cable		55
2206	PLASTHERM MY2-Y2 and MY2-EY2		56
2207	PLASTHERM 80 °C - PVC insulation and sheathing		58
2208	PLASTHERM 90 °C - PVC insulation and sheathing		59
2209	PLASTHERM 105 °C - PVC insulation and sheathing		60
2210	PLASTHERM 90 °C - Polyolefin insulation		61
2211	PLASTHERM PHF2 - Halogen-free insulation		62
2212	PLASTHERM PHF2E IRD - - Halogen-free insulation, reduced walls		63
2213	PLASTHERM PHFLEX - Cable resistant to alternate bending, halogen-free insulation		64
2214	PLASTHERM STYLE 21209 - Polyurethane sheathing		65
2215	PLASTHERM MYBE-EY-CSI - Intrinsic safety		66
2216	PLASTHERM HP-U - 2-conductor flat cable, thin insulation		67
2217	PLASTHERM HP-M - 2-conductor flat cable, thin insulation		68
2218	PLASTHERM HP-M-HT - 2-conductor flat cable, thin insulation		69

PLASTHERM® Y2 and EY2**-30 °C to +105 °C**

- 1 • Flexible bare (ref. Y2) or tin-plated (ref. EY2) copper core.
- 2 • Insulation: PVC 105 °C.

Applications

- Cabling in an environment potentially reaching +105°C (electrical appliances, light fittings, electronics, motor cars, etc.).

Options

- Solid bare (ref. RY2) or tin-plated (ref. REY2) copper core: see details of the option below.
- Extra-flexible bare (ref. Y2-ES) or tin-plated (ref. EY2-ES) copper core: see details of the option below.
- Silver-plated (ref. AY2) or nickel-plated (ref. CNY2) copper core: contact us.
 - Outer electrical shielding:
 - > Tin-plated copper braid: ref. Y2BE or EY2BE.
 - Insulation made of PVC 80°C: contact us.
 - Insulation made of PVC 125°C: contact us.
- Other nominal metric or American cross-sections: contact us.
- Other nominal stranding: contact us.
- Other options and/or combinations of the options outlined above: contact us.

Characteristics**General**

- Continuous operating temperatures: -30 °C to +105 °C.
- Good resistance to thermal shock.
- Good mechanical strength.
- Good resistance to common chemical environments.

Electrical

- Rated voltage: CS < 0.5 mm²: 300/500 V.
0.5 mm² ≤ CS < 1.5 mm²: 450/750 V.
CS ≥ 1.5 mm²: 600/1000 V.
- Test voltage: CS < 0.5 mm²: 1500 V.
0.5 mm² ≤ CS < 1.5 mm²: 2500 V.
CS ≥ 1.5 mm²: 3000 V.

Standard products

- Standard insulation colours: all colours including yellow/green.

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Y2 and EY2

Flexible core

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km) (Tin-plated copper core)
0.12	7 x 0.15*	161
0.14	7 x 0.16**	142
0.22	7 x 0.20	92.5
0.34	7 x 0.25	59.2
0.34	19 x 0.15*	58.9
0.38	19 x 0.16**	55.7
0.5	7 x 0.30	40.7
0.5	16 x 0.20	40.1
0.6	19 x 0.20	33.7
0.75	24 x 0.20	26.7
0.93	19 x 0.25	21.6
1	32 x 0.20	20.0
1.34	19 x 0.30	15.0
1.5	30 x 0.25	13.7
2.5	50 x 0.25	8.21
4	56 x 0.30	5.09
6	84 x 0.30	3.39
10	77 x 0.40	1.95
16	119 x 0.40	1.24

Option • RY2 and REY2

Solid core

0.22	1 x 0.52	85.9
0.34	1 x 0.64	54.1
0.5	1 x 0.80	36.7
0.75	1 x 0.98	24.8
1	1 x 1.13	18.2
1.5	1 x 1.38	12.2
2.5	1 x 1.77	7.56
4	1 x 2.24*	4.70
6	1 x 2.74*	3.11

Option • Y2-ES and EY2-ES

Extra-flexible core

0.05	24 x 0.05	405
0.14	70 x 0.05	159
0.25	130 x 0.05 or 60 x 0.07	86.6
0.34	180 x 0.05 or 90 x 0.07 or 40 x 0.10	59.9
0.4	200 x 0.05 or 100 x 0.07 or 50 x 0.10	50.7
0.5	260 x 0.05 or 130 x 0.07 or 60 x 0.10	40.7
0.75	390 x 0.05 or 200 x 0.07 or 100 x 0.10	27.1
1	520 x 0.05 or 260 x 0.07 or 120 x 0.10	20.4
1.5	750 x 0.05 or 390 x 0.07 or 190 x 0.10	13.7

* Nominal stranding only available in bare copper version.

** Nominal stranding only available in tin-plated copper version.

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.3	1.1	2.2
0.3	1.1	2.3
0.3	1.2	3.2
0.3	1.3	4.3
0.3	1.3	4.3
0.3	1.4	4.9
0.6	2.1	8.4
0.6	2.1	8.4
0.6	2.2	9.6
0.6	2.3	11.2
0.6	2.4	13.0
0.6	2.5	14.0
0.6	2.7	17.6
0.7	3.0	20.3
0.8	3.6	31.7
0.8	4.3	48.5
0.8	4.8	67.6
1.0	6.4	111
1.2	7.8	169

INSULATED WIRE

0.4	1.3	3.5
0.45	1.5	4.9
0.5	1.8	7.4
0.55	2.1	10.6
0.6	2.3	13.4
0.6	2.6	18.8
0.7	3.2	29.9
0.7	3.6	44.1
0.8	4.1	63.2

INSULATED WIRE

0.2	0.7	0.9
0.3	1.1	2.3
0.3	1.2	3.4
0.4	1.6	5.2
0.45	1.8	6.2
0.45	1.9	7.4
0.5	2.2	10.5
0.55	2.5	13.8
0.55	2.8	18.7

For this product, please contact:

OMERIN division principale

Zone Industrielle - F 63600 Ambert

Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10

omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.

For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® 80 °C

PVC insulation

UL and cUL approval



Characteristics

General

- Continuous operating temperatures -30°C to +80°C.
- Good resistance to chemical influences.
- Good alternate bending strength.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- All colours including two-coloured.
- Stranding of conducting cores: contact us.

Approvals - standards

- UL and cUL approval (CSA) as per standard UL 758 and C22.2 No. 210 – File no.: E101965.
- "Horizontal flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.

Applications

- Internal cabling for electrical or electronic appliances, computers, etc..

Options

- Other nominal cross-sections: contact us.
- Other style nos. available: styles no. 1017, 1019, 1020, 1021, 1022, 1023, 1158, 1159, 10024, 10076, 10127, 10437, 10438, 1498, 1662, 1908, 1909.



- 1 • Bare or tin-plated copper core.
- 2 • Insulation: PVC.

Style no.		1007		1497		1581	
Approval		80 °C – 300 V		80 °C – 300 V		80 °C – 300 V	
Nominal cross-section		Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)
AWG	(mm²)						
30	0.05	0.38	1.1	-	-	-	-
28	0.09	0.38	1.15	-	-	-	-
26	0.13	0.38	1.25	0.41	1.3	-	-
24	0.22	0.38	1.4	0.41	1.45	-	-
22	0.34	0.38	1.5	0.41	1.6	-	-
-	0.5	0.38	1.75	0.41	1.75	-	-
20	0.6	0.38	1.75	0.41	1.8	-	-
-	0.75	0.38	1.9	0.41	1.95	-	-
18	0.93	0.38	2.0	0.41	2.05	-	-
-	1	0.38	2.1	0.41	2.15	-	-
16	1.34	0.38	2.3	0.41	2.3	-	-
-	1.5	0.38	2.4	0.41	2.4	-	-
14	-	-	-	-	-	0.41	2.7
-	2.5	-	-	-	-	0.41	2.9
12	-	-	-	-	-	0.41	3.2
-	4	-	-	-	-	0.41	3.4
10	-	-	-	-	-	0.41	3.8
-	6	-	-	-	-	0.41	4.0
8	-	-	-	-	-	-	-
-	10	-	-	-	-	-	-
6	-	-	-	-	-	-	-
-	16	-	-	-	-	-	-
4	-	-	-	-	-	-	-
-	25	-	-	-	-	-	-
2	35	-	-	-	-	-	-
1	-	-	-	-	-	-	-
-	50	-	-	-	-	-	-
1/0	-	-	-	-	-	-	-
2/0	70	-	-	-	-	-	-
3/0	-	-	-	-	-	-	-
-	95	-	-	-	-	-	-
4/0	-	-	-	-	-	-	-
-	120	-	-	-	-	-	-
Conducting metal		BCDEFG		BCDEFG		BCDEFG	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.



Style no. 10053		1011		10381		1030			
Approval		80 °C – 300 V		80 °C – 600 V		80 °C – 600 V		80 °C – 1000 V	
Nominal cross-section		Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*	Average thickness of insulation	Nominal diameter*
AWG	(mm ²)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)
30	0.05	0.56	1.45	0.76	1.85	0.51	1.3	0.76	1.85
28	0.09	0.56	1.5	0.76	1.9	0.51	1.4	0.76	1.9
26	0.13	0.56	1.6	0.76	2.1	0.51	1.5	0.76	2.1
24	0.22	0.56	1.75	0.76	2.2	0.51	1.65	0.76	2.2
22	0.34	0.56	1.9	0.76	2.3	0.51	1.8	0.76	2.3
-	0.5	0.56	2.05	0.76	2.45	0.64	2.2	0.76	2.45
20	0.6	0.56	2.1	0.76	2.6	0.64	2.25	0.76	2.6
-	0.75	0.56	2.25	0.76	2.65	0.64	2.4	0.76	2.65
18	0.93	0.56	2.35	0.76	2.8	0.64	2.55	0.76	2.8
-	1	0.56	2.45	0.76	2.8	0.64	2.6	0.76	2.8
16	1.34	0.56	2.6	0.76	3.0	0.69	2.9	0.76	3.0
-	1.5	0.56	2.7	0.76	3.1	0.69	3.0	0.76	3.1
14	-	0.56	3.0	0.76	3.45	0.69	3.3	0.76	3.45
-	2.5	0.56	3.2	0.76	3.6	0.69	3.45	0.76	3.6
12	-	0.56	3.5	0.76	3.9	0.69	3.75	0.76	3.9
-	4	0.56	3.75	0.76	4.3	0.69	4.0	0.76	4.3
10	-	0.56	4.1	0.76	4.5	0.69	4.4	0.76	4.5
-	6	0.56	4.3	0.76	4.8	0.69	4.6	0.76	4.8
8	-	-	-	1.14	6.2	0.76	5.5	-	-
-	10	-	-	1.14	6.6	0.76	6.1	-	-
6	-	-	-	1.52	8.2	0.76	6.9	-	-
-	16	-	-	1.52	8.6	0.76	7.2	-	-
4	-	-	-	1.52	9.6	1.14	8.9	-	-
-	25	-	-	1.52	10.0	1.14	9.4	-	-
2	35	-	-	1.52	11.0	1.14	10.5	-	-
1	-	-	-	2.03	13.0	1.52	12.4	-	-
-	50	-	-	2.03	14.2	1.52	12.8	-	-
1/0	-	-	-	2.03	14.6	1.52	13.5	-	-
2/0	70	-	-	2.03	16.2	1.52	14.6	-	-
3/0	-	-	-	2.03	17.6	1.52	16.2	-	-
-	95	-	-	2.03	17.8	1.52	16.3	-	-
4/0	-	-	-	2.03	19.1	2.03	19.1	-	-
-	120	-	-	2.03	20.5	2.03	20.5	-	-
Conducting metal		BCDEFG		BCDEFG		BCDEFG		BCDEFG	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

For this product, please contact:

OMERIN division principale ✓
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® 105 °C

PVC insulation

UL and cUL approval



- 1 • Bare or tin-plated copper core.
- 2 • Insulation: PVC.

Characteristics

General

- Continuous operating temperatures -30°C to +105 °C.
- Good resistance to chemical influences.
- Good alternate bending strength.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- All colours including two-coloured.
- Stranding of conducting cores: contact us.

Approvals - standards

- UL and cUL approval (CSA) as per standard UL 758 and C22.2 No. 210 – File no.: E101965.
- "Horizontal flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.

Applications

- Internal cabling for electrical or electronic appliances, computers, etc..

Options

- Other nominal cross-sections: contact us.
- Other style nos. available: styles no. 1028, 1484, 1500, 1504, 1647, 1650, 10070, 10236, 11122, 11287.
- Available PVC 90 °C insulated style nos.: styles no. 1706, 1013, 1024, 1026, 1027, 1207, 1499, 10321, 1032, 1444: contact us.
- Nylon sleeving for certain Style number, consult us.
- Vertical flame test VW1 for style 1015: consult us.

Style no.	1569-VW-1	10198	1896	10012
Approval	105 °C – 300 V	105 °C – 300 V	105 °C – 300 V	105 °C – 600 V

Nominal cross-section		Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)
AWG	(mm ²)								
30	0.05	0.38	1.1	0.38	1.1	-	-	0.51	1.3
28	0.09	0.38	1.15	0.38	1.15	-	-	0.51	1.4
26	0.13	0.38	1.2	0.38	1.25	0.89	2.3	0.51	1.5
24	0.22	0.38	1.4	0.38	1.4	0.89	2.4	0.51	1.65
22	0.34	0.38	1.6	0.38	1.5	0.89	2.55	0.51	1.8
-	0.5	0.38	1.7	0.38	1.7	0.89	2.7	0.51	1.95
20	0.6	0.38	1.8	0.38	1.75	0.89	2.75	0.51	2.0
-	0.75	0.38	1.9	0.38	1.9	0.89	2.9	0.51	2.15
18	0.93	0.38	2.05	0.38	2.0	0.89	3.1	0.51	2.25
-	1	0.38	2.1	0.38	2.1	0.89	3.1	0.51	2.35
16	1.34	0.38	2.3	0.38	2.3	0.89	3.4	0.51	2.5
-	1.5	0.38	2.4	0.38	2.4	0.89	3.4	0.51	2.7
14	-	0.38	2.7	0.51	2.9	0.89	3.7	0.51	2.9
-	2.5	0.38	2.8	0.51	3.1	0.89	3.9	0.51	3.1
12	-	0.38	3.2	0.51	3.4	0.89	4.3	0.51	3.4
-	4	0.38	3.4	0.51	3.65	0.89	4.5	0.51	3.65
10	-	0.38	3.8	0.51	4.0	0.89	4.9	0.51	4.0
-	6	0.38	4.0	0.51	4.2	0.89	5.1	0.51	4.2
8	-	0.76	5.5	0.76	5.5	0.89	5.8	0.76	5.5
-	10	0.76	6.1	0.76	6.1	0.89	6.4	0.76	6.1
6	-	0.76	6.9	0.76	6.9	0.89	7.1	1.14	7.6
-	16	0.76	7.2	0.76	7.2	0.89	7.4	1.14	7.7
4	-	0.76	8.1	0.76	8.1	0.89	8.4	1.14	8.9
-	25	0.76	8.6	0.76	8.6	0.89	9.0	1.14	9.4
2	35	0.76	9.7	0.76	9.7	0.89	10.0	1.14	10.5
1	-	-	-	1.02	11.4	0.89	11.2	1.52	12.4
-	50	-	-	1.02	11.8	0.89	11.5	1.52	12.8
1/0	-	-	-	1.02	12.5	0.89	12.2	1.52	13.5
2/0	70	-	-	1.27	14.1	0.89	13.3	1.52	14.6
3/0	-	-	-	1.27	15.7	0.89	14.9	1.52	16.2
-	95	-	-	1.27	15.8	0.89	15.1	1.52	16.3
4/0	-	-	-	1.27	17.3	0.89	16.5	-	-
-	120	-	-	1.27	17.6	0.89	16.8	-	-
Conducting metal		BCDEFG		BCDEFG		BF		BCDEFG	

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (e > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (e > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories. © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com



Style no.		1015		1283		1897		10914		10271		10269	
Approval		105 °C – 600 V		105 °C – 600 V		105 °C – 600 V		105 °C – 1 000 V		105 °C – 1 000 V		105 °C – 1 000 V	
Nominal cross-section		Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)	Average thickness of insulation (mm)	Nominal diameter* (mm)
AWG	(mm ²)												
30	0.05	0.76	1.85	-	-	-	-	-	-	0.51	1.3	0.76	1.85
28	0.09	0.76	1.9	-	-	-	-	0.38	1.15	0.51	1.4	0.76	1.9
26	0.13	0.76	2.1	-	-	0.89	2.3	0.38	1.2	0.51	1.5	0.76	2.1
24	0.22	0.76	2.2	-	-	0.89	2.4	0.38	1.4	0.51	1.65	0.76	2.2
22	0.34	0.76	2.3	-	-	0.89	2.55	0.38	1.6	0.51	1.75	0.76	2.3
-	0.5	0.76	2.45	-	-	0.89	2.7	0.38	1.7	0.51	1.95	0.76	2.45
20	0.6	0.76	2.6	-	-	0.89	2.75	0.38	1.8	0.51	2.0	0.76	2.5
-	0.75	0.76	2.65	-	-	0.89	2.9	0.38	1.9	0.51	2.15	0.76	2.65
18	0.93	0.76	2.8	-	-	0.89	3.2	0.38	2.05	0.51	2.3	0.76	2.8
-	1	0.76	2.8	-	-	0.89	3.2	0.38	2.1	0.51	2.35	0.76	2.8
16	1.34	0.76	3.0	-	-	0.89	3.4	0.38	2.3	0.51	2.5	0.76	3.1
-	1.5	0.76	3.1	-	-	0.89	3.4	0.38	2.4	0.51	2.7	0.76	3.1
14	-	0.76	3.45	-	-	0.89	3.7	0.38	2.7	0.51	2.9	0.76	3.5
-	2.5	0.76	3.6	-	-	0.89	3.9	0.38	2.8	0.51	3.1	0.76	3.6
12	-	0.76	3.9	-	-	0.89	4.4	0.38	3.2	0.51	3.4	0.76	3.9
-	4	0.76	4.3	-	-	0.89	4.5	0.51	3.65	0.51	3.65	0.76	4.3
10	-	0.76	4.5	-	-	0.89	4.9	0.51	4.0	0.51	4.0	0.76	4.5
-	6	0.76	4.8	-	-	0.89	5.1	0.76	4.8	0.51	4.2	0.76	4.8
8	-	1.14	6.2	1.52	7.0	0.89	5.8	0.76	5.5	0.76	5.5	1.14	6.2
-	10	1.14	6.6	1.52	7.6	0.89	6.4	0.76	6.1	0.76	6.1	1.14	6.6
6	-	1.52	8.2	1.52	8.2	0.89	7.1	0.76	6.9	1.14	7.6	1.52	8.2
-	16	1.52	8.6	1.52	8.6	0.89	7.4	0.76	7.2	1.14	7.7	1.52	8.6
4	-	1.52	9.6	1.52	9.6	0.89	8.4	1.0	8.6	1.14	8.9	1.52	9.6
-	25	1.52	10.0	1.52	10.0	0.89	9.0	1.0	9.1	1.14	9.4	1.52	10.0
2	35	1.52	11.4	1.52	11.0	0.89	10.0	1.0	10.2	1.14	10.5	1.52	11.1
1	-	2.03	13.0	-	-	0.89	11.2	1.27	11.9	1.52	12.4	2.03	13.0
-	50	2.03	14.2	-	-	0.89	11.5	1.27	12.3	1.52	12.8	2.03	14.2
1/0	-	2.03	14.6	-	-	0.89	12.2	1.27	13.0	1.52	13.5	2.03	14.6
2/0	70	2.03	16.2	-	-	0.89	13.3	1.27	14.1	1.52	14.6	2.03	16.2
3/0	-	2.03	17.6	-	-	0.89	14.9	1.27	15.7	1.52	16.2	2.03	17.6
-	95	2.03	17.8	-	-	0.89	15.1	1.27	15.8	1.52	16.3	2.03	17.8
4/0	-	2.03	19.1	-	-	0.89	16.5	1.27	17.3	-	-	2.03	19.1
-	120	2.03	20.5	-	-	0.89	16.8	1.52	19.5	-	-	2.03	20.5

Conducting metal

BCDEFG

BCDEFG

BCDEFG

BCDEFG

BCDEFG

BCDEFG

KEY

- Conducting metals
- B Tin-plated copper
- B* Tin-plated copper (ø > 0.38 mm)
- C Nickel-plated copper
- D Silver-plated copper
- E Nickel
- F Bare copper
- F* Bare copper (ø > 0.38 mm)
- G Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

For this product, please contact:

OMERIN division principale ✓
 Zone Industrielle - F 63600 Ambert
 Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
 omerin@omerin.com

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
 © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® Style 1015-HAR

UL, cUL and USE <HAR> approval
-30 °C to +105 °C



- 1 • Flexible bare copper core – class 5 as per IEC 60228.
- 2 • Insulation: PVC - type T13 - NF C 32-525-1 / NF EN 50525-1 / EN 50363-3.

Approvals - standards

- UL approval as per standard UL 758
File no.: E101965.
- cUL approval (up to 4 mm² included)
as per standard CSA C22.2 N° 210 -
File no.: E101965.
- USE <HAR> approval
as per NF EN 50525-2-31.
- "Horizontal flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.
- Resistance to vertical flame propagation
for a single insulated wire: IEC 60332-1-2 /
EN 50265-2-1 / NF C 32-070 test C2.

Applications

- Internal cabling for electrical and
electronic appliances.

Options

- Tin-plated copper core.

Style 1015-HAR

Flexible core • class 5 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
Type H05V2-K		
0.5	16 x 0.20	39.0
0.75	24 x 0.20	26.0
1	32 x 0.20	19.5
Type H07V2-K		
1.5	30 x 0.25	13.3
2.5	50 x 0.25	7.98
4	56 x 0.30	4.95
6	84 x 0.30	3.30
10	80 x 0.40	1.91
16*	126 x 0.40	1.21
25	192 x 0.40	0.78
35	259 x 0.40	0.554

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
Type H05V2-K		
0.76	2.45	9.9
0.76	2.65	12.6
0.76	2.8	15.1
Type H07V2-K		
0.76	3.1	20.1
0.80	3.6	30.1
0.80	4.3	46.8
0.80	4.8	65.2
1.15	6.6	117
1.15	7.7	168
1.52	10.0	274
1.52	11.4	359

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

* Nominal cross-section only available in Style 10271 <HAR>.

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® style 20199

2-conductor flat cable

105°C PVC insulation

UL approval

-30 °C to +105 °C



Approvals - standards

- UL approval as per standard UL 758 - File no.: E101965.

Applications

- Internal cabling for electric, electronic, audio and video appliances.

Options

- Identification using a coloured longitudinal stripe on one of the two conductors: contact us.

Characteristics

General

- Continuous operating temperatures: -30 °C to +105 °C.
- Very good flexibility.
- Good alternate bending strength.
- Easy stripping and separating of conductors.

Electrical

- Rated voltage: 300 V.
- Test voltage: as per standard UL 758.

Standard products

- Standard insulation colour: white.
- Identification by marking on one of the two conductors.



- 1 • Flexible bare or tin-plated copper core.
- 2 • Insulation: PVC 105 °C.


Style 20199

FLEXIBLE CORE

Nominal cross-section AWG	Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km) (bare copper core)
2 x 24	2 x 0.22	7 x 0.20	87.6
2 x 22	2 x 0.34	7 x 0.25	55.4
-	2 x 0.5	16 x 0.20	39.0
2 x 20	2 x 0.6	19 x 0.20	34.6

INSULATED CABLE

Nominal outer dimensions (mm)		Approximate linear weight (kg/km)
a	b	
1.4	3.0	7.5
1.5	3.2	9.8
1.7	3.6	13.0
1.7	3.6	15.7



For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM®

MY2-Y2 and MY2-EY2

-30 °C to +105 °C



- 1 • Flexible bare (ref. MY2-Y2) or tin-plated (ref. MY2-EY2) copper core.
- 2 • Insulation: PVC 105 °C.
- 3 • Outer sheath: PVC 105 °C.

Applications

- Cabling in an environment potentially reaching +105°C (electrical appliances, light fittings, electronics, motor cars, etc.).

Options

- Silver-plated (ref. MY2-AY2) or nickel-plated (ref. MY2-CNY2) copper core: contact us.
 - Electrical shielding:
 - > Tin-plated copper braid: ref. MY2BE-Y2 or MY2BE-EY2.
 - > Aluminium tape + continuity wire: ref. MY2BAL-Y2 or MY2BAL-EY2.
 - Insulation and/or outer sheath made of PVC 80°C: contact us.
 - Insulation and/or outer sheath made of PVC 125 °C: contact us.
 - Insulation made of silicone rubber: contact us.
- Insulation made of fluorinated polymer ETFE, FEP or PFA: contact us.
 - Other nominal metric or American cross-sections: contact us.
 - Other nominal stranding: contact us.
 - Other outer sheath colours: contact us.
 - Other options and/or combinations of the options outlined above: contact us.
- Other numbers of conductors: contact us.

Characteristics

General

- Continuous operating temperatures: -30 °C to +105 °C.
- Good resistance to thermal shock.
- Good mechanical strength.
- Good resistance to common chemical environments.

Electrical

- Rated voltage: up to 600/1000 V.
- Test voltage: up to 3000 V.

Standard products

- Standard conductor colours: see table below.
- Standard outer sheath colours: grey or black.

Standard conductor colours:

Number of conductors	With an earth wire	Without an earth wire
2	-	blue – brown
3	yellow/green – blue – brown	brown – black – grey
4	yellow/green – brown – black – grey	blue – brown – black – grey
5	yellow/green – blue – brown – black – grey	blue – brown – black – grey – black
≥6	yellow/green – grey numbered	grey numbered

Identification

Multi-conductor cables without an earth wire are identified as follows:

< Number of conductors > X < Cross-section > (mm²) (example: 3 X 1.5 mm²).

Multi-conductor cables with an earth wire are identified by the symbol G in the place of the X (example 3 G 1.5 mm²).

Flexible core • class 5 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
2 x 0.22	7 x 0.20	92.5
3 x 0.22	7 x 0.20	92.5
4 x 0.22	7 x 0.20	92.5
5 x 0.22	7 x 0.20	92.5
7 x 0.22	7 x 0.20	92.5
19 x 0.22	7 x 0.20	92.5
2 x 0.34	7 x 0.25	59.2
3 x 0.34	7 x 0.25	59.2
4 x 0.34	7 x 0.25	59.2
5 x 0.34	7 x 0.25	59.2
7 x 0.34	7 x 0.25	59.2
19 x 0.34	7 x 0.25	59.2

INSULATED CONDUCTORS

Nominal thickness of insulation (mm)	Nominal diameter (mm)
0.3	1.2
0.3	1.2
0.3	1.2
0.3	1.2
0.3	1.2
0.3	1.2
0.4	1.6
0.4	1.6
0.4	1.6
0.4	1.6
0.4	1.6
0.4	1.6

SHEATHED CABLE

Nominal diameter (mm)	Approximate linear weight (kg/km)
3.4	14.8
3.6	17.7
3.9	21.2
4.4	26.9
4.8	34.2
7.6	84.4
4.4	24.3
4.7	29.0
5.1	34.8
5.5	41.1
6.0	52.9
9.6	132

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Flexible core • class 5 as per IEC 60228

INSULATED CONDUCTORS

SHEATHED CABLE

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)	INSULATED CONDUCTORS		SHEATHED CABLE	
			Nominal thickness of insulation (mm)	Nominal diameter (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
2 x 0.5	16 x 0.20	40.1	0.4	1.8	4.8	30.0
3 x 0.5	16 x 0.20	40.1	0.4	1.8	5.1	36.4
4 x 0.5	16 x 0.20	40.1	0.4	1.8	5.5	44.1
5 x 0.5	16 x 0.20	40.1	0.4	1.8	6.1	52.4
7 x 0.5	16 x 0.20	40.1	0.4	1.8	6.6	68.0
19 x 0.5	16 x 0.20	40.1	0.4	1.8	11.0	180
2 x 0.6	19 x 0.20	33.7	0.6	2.2	5.6	39.5
3 x 0.6	19 x 0.20	33.7	0.6	2.2	6.0	47.8
4 x 0.6	19 x 0.20	33.7	0.6	2.2	6.5	57.8
5 x 0.6	19 x 0.20	33.7	0.6	2.2	7.5	75.2
7 x 0.6	19 x 0.20	33.7	0.6	2.2	8.2	96.7
19 x 0.6	19 x 0.20	33.7	0.6	2.2	13.2	243
2 x 0.75	24 x 0.20	26.7	0.6	2.3	5.8	43.7
3 x 0.75	24 x 0.20	26.7	0.6	2.3	6.2	53.4
4 x 0.75	24 x 0.20	26.7	0.6	2.3	6.7	65.0
5 x 0.75	24 x 0.20	26.7	0.6	2.3	7.8	84.2
7 x 0.75	24 x 0.20	26.7	0.6	2.3	8.5	109
19 x 0.75	24 x 0.20	26.7	0.6	2.3	13.7	275
2 x 0.93	19 x 0.25	21.6	0.6	2.4	6.0	48.8
3 x 0.93	19 x 0.25	21.6	0.6	2.4	6.4	60.2
4 x 0.93	19 x 0.25	21.6	0.6	2.4	7.0	73.7
5 x 0.93	19 x 0.25	21.6	0.6	2.4	8.1	95.1
7 x 0.93	19 x 0.25	21.6	0.6	2.4	8.8	124
19 x 0.93	19 x 0.25	21.6	0.6	2.4	14.2	314
2 x 1	32 x 0.20	20.0	0.6	2.5	6.2	51.9
3 x 1	32 x 0.20	20.0	0.6	2.5	6.6	64.1
4 x 1	32 x 0.20	20.0	0.6	2.5	7.6	84.9
5 x 1	32 x 0.20	20.0	0.6	2.5	8.4	101
7 x 1	32 x 0.20	20.0	0.6	2.5	9.1	132
19 x 1	32 x 0.20	20.0	0.6	2.5	14.7	334
2 x 1.34	19 x 0.30	15.0	0.6	2.7	6.6	62.0
3 x 1.34	19 x 0.30	15.0	0.6	2.7	7.0	77.5
4 x 1.34	19 x 0.30	15.0	0.6	2.7	8.1	102
5 x 1.34	19 x 0.30	15.0	0.6	2.7	8.9	122
7 x 1.34	19 x 0.30	15.0	0.6	2.7	9.7	161
2 x 1.5	30 x 0.25	13.7	0.6	2.8	6.8	66.0
3 x 1.5	30 x 0.25	13.7	0.6	2.8	7.6	89.1
4 x 1.5	30 x 0.25	13.7	0.6	2.8	8.3	109
5 x 1.5	30 x 0.25	13.7	0.6	2.8	9.2	131
7 x 1.5	30 x 0.25	13.7	0.6	2.8	10.0	172
2 x 2.5	50 x 0.25	8.21	0.7	3.4	8.4	104
3 x 2.5	50 x 0.25	8.21	0.7	3.4	8.9	131
4 x 2.5	50 x 0.25	8.21	0.7	3.4	9.8	162
5 x 2.5	50 x 0.25	8.21	0.7	3.4	11.2	204
7 x 2.5	50 x 0.25	8.21	0.7	3.4	12.2	269
2 x 4	56 x 0.30	5.09	0.8	4.2	10.0	153
3 x 4	56 x 0.30	5.09	0.8	4.2	11.1	205
4 x 4	56 x 0.30	5.09	0.8	4.2	12.1	253
5 x 4	56 x 0.30	5.09	0.8	4.2	13.5	311
7 x 4	56 x 0.30	5.09	0.8	4.2	14.8	412
2 x 6	84 x 0.30	3.39	0.8	4.8	11.6	216
3 x 6	84 x 0.30	3.39	0.8	4.8	12.4	276
4 x 6	84 x 0.30	3.39	0.8	4.8	13.8	350
5 x 6	84 x 0.30	3.39	0.8	4.8	15.8	444
7 x 6	84 x 0.30	3.39	0.8	4.8	17.2	588
2 x 10	77 x 0.40	1.95	1.0	6.4	15.0	350
3 x 10	77 x 0.40	1.95	1.0	6.4	16.6	468
4 x 10	77 x 0.40	1.95	1.0	6.4	18.2	581
5 x 10	77 x 0.40	1.95	1.0	6.4	19.9	693
7 x 10	77 x 0.40	1.95	1.0	6.4	21.8	926
2 x 16	119 x 0.40	1.24	1.2	7.8	18.4	532
3 x 16	119 x 0.40	1.24	1.2	7.8	19.6	681
4 x 16	119 x 0.40	1.24	1.2	7.8	21.4	840
5 x 16	119 x 0.40	1.24	1.2	7.8	23.7	1019
7 x 16	119 x 0.40	1.24	1.2	7.8	26.2	1382

PLASTHERM® 80 °C

PVC insulation
PVC sheathing
UL and cUL approval



- 1 • UL and cUL approved conductors with PVC insulation.
- 2 • Outer sheath: PVC.

Characteristics

General

- Continuous operating temperatures: -30 °C to +80 °C.
- Good resistance to common chemical environments.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- Single conductors: UL and cUL approved PVC insulated conductors (≥ 80 °C).
- Standard outer sheath colours: black or grey.
- Stranding of conducting cores: contact us.

Approvals - standards

- UL approval as per standard UL 758 - File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 - File no.: E101965.
- "Cable flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.

Applications

- External or internal cabling for electrical appliances.

Options

- Electrical shielding: Tin-plated copper braid, or aluminium tape + continuity wire.
- Other outer sheath colours: contact us.
- Other nominal cross-sections: contact us.
- Other style nos. available: styles no. 20871, 21061, 21047, 2610, 2655, 2656, 20212, 20295, 2463, 20207, 21058.

KEY

- Conducting metals
- B** Tin-plated copper
- B*** Tin-plated copper (ø > 0.38 mm)
- C** Nickel-plated copper
- D** Silver-plated copper
- E** Nickel
- F** Bare copper
- F*** Bare copper (ø > 0.38 mm)
- G** Nickel-plated copper 27 %

- AWM I A** Internal wiring, not subject to mechanical abuse
- AWM I A/B** Internal wiring
- AWM II A/B** External or Internal wiring

- NS** Not Specified
- VNS** Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core.
Only the average thickness of insulation or the sheathing should be taken into account.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com



www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Style no.	2464-Y80		2570-Y80	
	Approval		Approval	
	80 °C - 300 V		80 °C - 600 or 1000 V	
	AWM II A/B		AWM II A/B	
No. of cond.	Nominal cross-section (mm ²)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)
2	26	0.13	1.25	4.0
3	26	0.13	1.25	4.2
4	26	0.13	1.25	4.5
5	26	0.13	1.25	4.9
7	26	0.13	1.25	5.3
2	24	0.22	1.4	4.3
3	24	0.22	1.4	4.5
4	24	0.22	1.4	4.9
5	24	0.22	1.4	5.3
7	24	0.22	1.4	5.7
2	22	0.34	1.5	4.5
3	22	0.34	1.5	4.8
4	22	0.34	1.5	5.1
5	22	0.34	1.5	5.6
7	22	0.34	1.5	6.0
2	-	0.5	1.75	5.0
3	-	0.5	1.75	5.3
4	-	0.5	1.75	5.7
5	-	0.5	1.75	6.2
7	-	0.5	1.75	6.8
2	20	0.6	1.75	5.0
3	20	0.6	1.75	5.3
4	20	0.6	1.75	5.7
5	20	0.6	1.75	6.2
7	20	0.6	1.75	6.8
2	-	0.75	1.9	5.3
3	-	0.75	1.9	5.6
4	-	0.75	1.9	6.1
5	-	0.75	1.9	6.7
7	-	0.75	1.9	7.2
2	18	0.93	2.0	5.5
3	18	0.93	2.0	5.8
4	18	0.93	2.0	6.3
5	18	0.93	2.0	6.9
7	18	0.93	2.0	7.5
2	-	1	2.1	5.7
3	-	1	2.1	6.1
4	-	1	2.1	6.6
5	-	1	2.1	7.2
7	-	1	2.1	7.8
2	16	1.34	2.3	6.1
3	16	1.34	2.3	6.5
4	16	1.34	2.3	7.1
5	16	1.34	2.3	7.7
7	16	1.34	2.3	8.4
2	-	1.5	2.4	6.3
3	-	1.5	2.4	6.7
4	-	1.5	2.4	7.3
5	-	1.5	2.4	8.0
7	-	1.5	2.4	8.7
2	14	-	2.7	6.9
3	14	-	2.7	7.4
4	14	-	2.7	8.0
5	14	-	2.7	8.8
7	14	-	2.7	9.6
2	-	-	2.7	6.9
3	-	-	2.7	7.4
4	-	-	2.7	8.0
5	-	-	2.7	8.8
7	-	-	2.7	9.6
2	-	-	2.7	6.9
3	-	-	2.7	7.4
4	-	-	2.7	8.0
5	-	-	2.7	8.8
7	-	-	2.7	9.6

Conducting metal

BCDEFG

BCDEFG

PLASTHERM® 90 °C

PVC insulation
PVC sheathing
UL and cUL approval



- 1 • UL and cUL approved conductors with PVC insulation.
- 2 • Outer sheath: PVC.

Characteristics General

- Continuous operating temperatures: -30 °C to +90 °C.
- Good resistance to common chemical environments.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- Single conductors: UL and cUL approved PVC insulated conductors (≥ 90 °C).
- Standard outer sheath colours: black or grey.
- Stranding of conducting cores: contact us.

Approvals - standards

- UL approval as per standard UL 758 - File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 - File no.: E101965.
- "Cable flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.

Applications

- External or internal cabling for electrical appliances.

Options

- Electrical shielding: Tin-plated copper braid, or aluminium tape + continuity wire.
- Other outer sheath colours: contact us.
- Other nominal cross-sections: contact us.
- Other style nos. available: styles no. 2549, 20132, 2550, 2653.

KEY

- Conducting metals
- B** Tin-plated copper
- B*** Tin-plated copper (ø > 0.38 mm)
- C** Nickel-plated copper
- D** Silver-plated copper
- E** Nickel
- F** Bare copper
- F*** Bare copper (ø > 0.38 mm)
- G** Nickel-plated copper 27 %

AWM I A Internal wiring, not subject to mechanical abuse

AWM I A/B Internal wiring
AWM II A/B External or Internal wiring

NS Not Specified
VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation or the sheathing should be taken into account.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com



www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Style no. 2654-Y90			Approval 90 °C - 300 V		Style no. 2587-Y90		Approval 90 °C - 600 V	
			AWM II A/B				AWM II A/B	
No. of cond.	AWG	Nominal cross-section (mm²)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)
2	26	0.13	1.2	3.9	2.1	5.7	2.1	6.1
3	26	0.13	1.2	4.1	2.1	6.1	2.1	6.6
4	26	0.13	1.2	4.4	2.1	6.6	2.1	7.2
5	26	0.13	1.2	4.8	2.1	7.2	2.1	7.8
7	26	0.13	1.2	5.1	2.1	7.8	2.1	8.4
2	24	0.22	1.4	4.3	2.2	5.9	2.2	6.3
3	24	0.22	1.4	4.5	2.2	6.3	2.2	6.8
4	24	0.22	1.4	4.9	2.2	6.8	2.2	7.5
5	24	0.22	1.4	5.3	2.2	7.5	2.2	8.1
7	24	0.22	1.4	5.7	2.2	8.1	2.2	8.7
2	22	0.34	1.6	4.7	2.3	6.1	2.3	6.5
3	22	0.34	1.6	5.0	2.3	6.5	2.3	7.1
4	22	0.34	1.6	5.4	2.3	7.1	2.3	7.7
5	22	0.34	1.6	5.8	2.3	7.7	2.3	8.4
7	22	0.34	1.6	6.3	2.3	8.4	2.3	9.1
2	-	0.5	1.7	4.9	2.45	6.4	2.45	6.8
3	-	0.5	1.7	5.2	2.45	6.8	2.45	7.4
4	-	0.5	1.7	5.6	2.45	7.4	2.45	8.1
5	-	0.5	1.7	6.1	2.45	8.1	2.45	8.9
7	-	0.5	1.7	6.6	2.45	8.9	2.45	9.7
2	20	0.6	1.8	5.1	2.6	6.7	2.6	7.1
3	20	0.6	1.8	5.4	2.6	7.1	2.6	7.8
4	20	0.6	1.8	5.9	2.6	7.8	2.6	8.5
5	20	0.6	1.8	6.4	2.6	8.5	2.6	9.3
7	20	0.6	1.8	6.9	2.6	9.3	2.6	10.1
2	-	0.75	1.9	5.3	2.65	6.8	2.65	7.2
3	-	0.75	1.9	5.6	2.65	7.2	2.65	7.9
4	-	0.75	1.9	6.1	2.65	7.9	2.65	8.7
5	-	0.75	1.9	6.7	2.65	8.7	2.65	9.5
7	-	0.75	1.9	7.2	2.65	9.5	2.65	10.3
2	18	0.93	2.05	5.6	2.8	7.1	2.8	7.6
3	18	0.93	2.05	5.9	2.8	7.6	2.8	8.3
4	18	0.93	2.05	6.5	2.8	8.3	2.8	9.1
5	18	0.93	2.05	7.1	2.8	9.1	2.8	9.9
7	18	0.93	2.05	7.7	2.8	9.9	2.8	10.7
2	-	1	2.1	5.7	2.8	7.1	2.8	7.6
3	-	1	2.1	6.1	2.8	7.6	2.8	8.3
4	-	1	2.1	6.6	2.8	8.3	2.8	9.1
5	-	1	2.1	7.2	2.8	9.1	2.8	9.9
7	-	1	2.1	7.8	2.8	9.9	2.8	10.7
2	16	1.34	2.3	6.1	3.0	7.5	3.0	8.0
3	16	1.34	2.3	6.5	3.0	8.0	3.0	8.8
4	16	1.34	2.3	7.1	3.0	8.8	3.0	9.6
5	16	1.34	2.3	7.7	3.0	9.6	3.0	10.5
7	16	1.34	2.3	8.4	3.0	10.5	3.0	11.3
2	-	1.5	2.4	6.3	3.1	7.7	3.1	8.2
3	-	1.5	2.4	6.7	3.1	8.2	3.1	9.0
4	-	1.5	2.4	7.3	3.1	9.0	3.1	9.9
5	-	1.5	2.4	8.0	3.1	9.9	3.1	10.8
7	-	1.5	2.4	8.7	3.1	10.8	3.1	11.7
2	14	-	2.7	6.9	3.45	8.4	3.45	9.0
3	14	-	2.7	7.4	3.45	9.0	3.45	9.8
4	14	-	2.7	8.0	3.45	9.8	3.45	10.8
5	14	-	2.7	8.8	3.45	10.8	3.45	11.9
7	14	-	2.7	9.6	3.45	11.9	3.45	13.1

Conducting metal

BCDEFG

BCDEFG

PLASTHERM® 105 °C

PVC insulation
PVC sheathing
UL and cUL approval



- 1 • UL and cUL approved conductors with PVC insulation.
- 2 • Outer sheath: PVC.

Characteristics

- General**
- Continuous operating temperatures: -30 °C to +105 °C.
 - Good resistance to common chemical environments.
- Electrical**
- Rated voltage: as per style no.
 - Test voltage: 10 x Rated voltage.

Standard products

- Single conductors: UL and cUL approved PVC insulated conductors (≥ 105 °C).
- Outer sheath colours: black or grey.
- Stranding of conducting cores: contact us.

Approvals - standards

- UL approval as per standard UL 758 - File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 - File no.: E101965.
- "Cable flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.

Applications

- External or internal cabling for electrical appliances.

Options

- Electrical shielding: Tin-plated copper braid, or aluminium tape + continuity wire.
- Other outer sheath colours: contact us.
- Other nominal cross-sections: contact us.
- Other style nos. available: styles no. 2589, 2661, 2662, 2501, 2516, 2907, 20155, 20213, 20214, 20811, 20883, 20903.
- Vertical flame test VW-1 for styles 2517 300V, 2586 600V and 2586 1000 V: please consult us.

KEY

- Conducting metals
- B** Tin-plated copper
- B*** Tin-plated copper (ø > 0.38 mm)
- C** Nickel-plated copper
- D** Silver-plated copper
- E** Nickel
- F** Bare copper
- F*** Bare copper (ø > 0.38 mm)
- G** Nickel-plated copper 27 %

- AWM I A** Internal wiring, not subject to mechanical abuse
- AWM I A/B** Internal wiring
- AWM II A/B** External or Internal wiring

- NS** Not Specified
- VNS** Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core.
Only the average thickness of insulation or the sheathing should be taken into account.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com



www.omerin.com

Conducting metal

BCDEFG

BCDEFG

BCDEFG

Style no.	Approval	105 °C - 300 V				105 °C - 600 V		105 °C - 1000 V	
		AWM II A/B				AWM II A/B		AWM II A/B	
		Nominal cross-section	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)	
2	26	0.13	1.2	3.9	2.1	5.7	2.1	5.7	
3	26	0.13	1.2	4.1	2.1	6.1	2.1	6.1	
4	26	0.13	1.2	4.4	2.1	6.6	2.1	6.6	
5	26	0.13	1.2	4.8	2.1	7.2	2.1	7.2	
7	26	0.13	1.2	5.1	2.1	7.8	2.1	7.8	
2	24	0.22	1.4	4.3	2.2	5.9	2.2	5.9	
3	24	0.22	1.4	4.5	2.2	6.3	2.2	6.3	
4	24	0.22	1.4	4.9	2.2	6.8	2.2	6.8	
5	24	0.22	1.4	5.3	2.2	7.5	2.2	7.5	
7	24	0.22	1.4	5.7	2.2	8.1	2.2	8.1	
2	22	0.34	1.6	4.7	2.3	6.1	2.3	6.1	
3	22	0.34	1.6	5.0	2.3	6.5	2.3	6.5	
4	22	0.34	1.6	5.4	2.3	7.1	2.3	7.1	
5	22	0.34	1.6	5.8	2.3	7.7	2.3	7.7	
7	22	0.34	1.6	6.3	2.3	8.4	2.3	8.4	
2	-	0.5	1.7	4.9	2.45	6.4	2.45	6.4	
3	-	0.5	1.7	5.2	2.45	6.8	2.45	6.8	
4	-	0.5	1.7	5.6	2.45	7.4	2.45	7.4	
5	-	0.5	1.7	6.1	2.45	8.1	2.45	8.1	
7	-	0.5	1.7	6.6	2.45	8.9	2.45	8.9	
2	20	0.6	1.8	5.1	2.6	6.7	2.6	6.7	
3	20	0.6	1.8	5.4	2.6	7.1	2.6	7.1	
4	20	0.6	1.8	5.9	2.6	7.8	2.6	7.8	
5	20	0.6	1.8	6.4	2.6	8.5	2.6	8.5	
7	20	0.6	1.8	6.9	2.6	9.3	2.6	9.3	
2	-	0.75	1.9	5.3	2.65	6.8	2.65	6.8	
3	-	0.75	1.9	5.6	2.65	7.2	2.65	7.2	
4	-	0.75	1.9	6.1	2.65	7.9	2.65	7.9	
5	-	0.75	1.9	6.7	2.65	8.7	2.65	8.7	
7	-	0.75	1.9	7.2	2.65	9.5	2.65	9.5	
2	18	0.93	2.05	5.6	2.8	7.1	2.8	7.1	
3	18	0.93	2.05	5.9	2.8	7.6	2.8	7.6	
4	18	0.93	2.05	6.5	2.8	8.3	2.8	8.3	
5	18	0.93	2.05	7.1	2.8	9.1	2.8	9.1	
7	18	0.93	2.05	7.7	2.8	9.9	2.8	9.9	
2	-	1	2.1	5.7	2.8	7.1	2.8	7.1	
3	-	1	2.1	6.1	2.8	7.6	2.8	7.6	
4	-	1	2.1	6.6	2.8	8.3	2.8	8.3	
5	-	1	2.1	7.2	2.8	9.1	2.8	9.1	
7	-	1	2.1	7.8	2.8	9.9	2.8	9.9	
2	16	1.34	2.3	6.1	3.0	7.5	3.1	7.7	
3	16	1.34	2.3	6.5	3.0	8.0	3.1	8.2	
4	16	1.34	2.3	7.1	3.0	8.8	3.1	9.0	
5	16	1.34	2.3	7.7	3.0	9.6	3.1	9.9	
7	16	1.34	2.3	8.4	3.0	10.5	3.1	10.8	
2	-	1.5	2.4	6.3	3.1	7.7	3.1	7.7	
3	-	1.5	2.4	6.7	3.1	8.2	3.1	8.2	
4	-	1.5	2.4	7.3	3.1	9.0	3.1	9.0	
5	-	1.5	2.4	8.0	3.1	9.9	3.1	9.9	
7	-	1.5	2.4	8.7	3.1	10.8	3.1	10.8	
2	14	-	2.7	6.9	3.45	8.4	3.5	8.5	
3	14	-	2.7	7.4	3.45	9.0	3.5	9.1	
4	14	-	2.7	8.0	3.45	9.8	3.5	10.0	
5	14	-	2.7	8.8	3.45	10.8	3.5	11.0	
7	14	-	2.7	9.6	3.45	11.9	3.5	12.0	

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories. © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® 90 °C

Polyolefin insulation

UL and cUL approval



Characteristics

General

- Continuous operating temperatures: -20 °C to +90 °C.
- Good resistance to chemical influences.

Electrical

- Rated voltage: 600 V.
- Test voltage: 6,000 V.

Standard products

- All colours including two-coloured.
- Stranding of conducting cores: contact us.

Approvals - standards

- UL approval as per standard UL758 and cUL approval (CSA) as per standard C22.2 No. 210, File no. E101 965.
- "Horizontal flame test" as per UL758 standard.

Applications

- Internal cabling for electrical appliances.

Options

- Other nominal cross-sections: contact us.

KEY

- conducting metals
- B** Tin-plated copper
- B*** Tin-plated copper (ø > 0.38 mm)
- C** Nickel-plated copper
- D** Silver-plated copper
- E** Nickel
- F** Bare copper
- F*** Bare copper (ø > 0.38 mm)
- G** Nickel-plated copper 27 %

- AWM I A Internal wiring, not subject to mechanical abuse
- AWM I A/B Internal wiring
- AWM II A/B External or Internal wiring

- NS Not Specified
- VNS Voltage Not Specified

■ : UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core.
Only the average thickness of insulation should be taken into account.



- 1 • Bare or tin-plated copper core.
- 2 • Insulation: polyolefin.

Style no. **10900**

Approval

90 °C – 600 V
AWM I A/B

Nominal cross-section		Average thickness of insulation (mm)	Nominal diameter* (mm)
AWG	(mm ²)		
30	0.05	0.38	1.1
28	0.09	0.38	1.1
26	0.13	0.38	1.2
24	0.22	0.38	1.4
22	0.34	0.38	1.5
-	0.5	0.38	1.7
20	0.6	0.38	1.75
-	0.75	0.38	1.9
18	0.93	0.38	2.0
-	1	0.76	2.9
16	1.34	0.76	3.0
-	1.5	0.76	3.1
14	-	0.76	3.4
-	2.5	0.76	3.6
12	-	0.76	3.9
-	4	0.76	4.2
10	-	0.76	4.5
-	6	0.76	4.7
8	-	0.76	5.5
-	10	0.76	6.1
6	-	0.76	6.9
-	16	0.76	7.2
4	-	0.76	8.1
-	25	0.76	8.6
2	35	0.76	9.7
1	-	1.52	12.4
-	50	1.52	12.8
1/0	-	1.52	13.5
2/0	70	1.52	14.6
3/0	-	1.52	16.2
-	95	1.52	16.3
4/0	-	1.52	18.1

Conducting metal **BF**

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. (33) 04 73 82 50 00 - Fax (33) 04 73 82 50 10
omerin@omerin.com

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
® Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® PHF2

Halogen-free insulation flame retardant

-40 °C to +105 °C

Approvals - standards

- Resistance to vertical flame propagation for a single insulated wire. IEC 60332-1-2 / NF C 32-070 test C2
- Tests on electric cables under fire conditions as per IEC 60332-3-22 (category A): ISSEP test reports no. 1524/2015
- Classification C1 as per NF C 32-070 test no. 1 (LCIE report no. 12/108571-616378A)
- Halogen-free, low corrosivity and acidity of gases evolved during combustion: EN 60754-1 and EN 60754-2
- Low smoke opacity: EN 61034-2

Applications

- Internal cabling for electrical and electronic appliances

Characteristics

General

- Continuous operating temperatures: -40 °C to +105 °C.
- Halogen-free, flame retardant, low toxicity, corrosivity and smoke opacity
- Good flexibility and mechanical strength, excellent resistance to abrasion.

Electrical


- Rated voltage: 600/1 000 V.
- Test voltage: 3 000 V.

Standard products

- All solid colours + two-coloured yellow/green

Options

- Solid bare copper core, class 1 as per IEC 60228: ref. PHF2R, see table below).
- American cross-sections AWG: Contact us



- 1 • Flexible bare copper (PHF2) or tin-plated (PHF2E) core – Class 5 as per IEC 60228.
- 2 • Halogen-free, flame-retardant thermoplastic insulation.

PLASTHERM PHF2 and PHF2E

Flexible core • class 5 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)	
		PHF2	PHF2E
0.5	16 x 0.20	39.0	40.1
0.75	24 x 0.20	26.0	26.7
1	32 x 0.20	19.5	20.0
1.5	30 x 0.25	13.3	13.7
2.5	50 x 0.25	7.98	8.21
4	56 x 0.30	4.95	5.09
6	84 x 0.30	3.30	3.39
10	80 x 0.40	1.91	1.95
16	126 x 0.40	1.21	1.24
25	196 x 0.40	0.78	0.795
35	276 x 0.40	0.554	0.565
50	396 x 0.40	0.386	0.393
70	360 x 0.50	0.272	0.277
95	485 x 0.50	0.206	0.210
120	608 x 0.50	0.161	0.164
150	756 x 0.50	0.129	0.132
185	944 x 0.50	0.106	0.108
240	1221 x 0.50	0.0801	0.0817
300	1525 x 0.50	0.0641	0.0654

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.6	2.20	9.1
0.6	2.40	11.9
0.7	2.70	15.2
0.8	3.10	22.3
0.8	3.60	33.4
0.9	4.30	50.1
0.9	5.00	72.5
0.9	6.10	113
1.0	7.10	170
1.0	8.70	256
1.1	10.3	364
1.1	12.1	510
1.1	13.9	692
1.4	16.6	972
1.4	18.2	1202
1.6	20.2	1503
1.6	22.4	1849
1.8	25.4	2376
1.8	27.6	2909

Option: PLASTHERM PHF2R

Solid core • class 1 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.5	1 x 0.80	36.0
0.75	1 x 0.98	24.5
1	1 x 1.13	18.1
1.5	1 x 1.38	12.1
2.5	1 x 1.77	7.41
4	1 x 2.24	4.61

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.6	2.00	9.35
0.6	2.20	12.2
0.7	2.60	15.1
0.7	2.80	21.6
0.8	3.40	32.1
0.8	4.00	48.7

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. (33) 04 73 82 50 00 - Fax (33) 04 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.

For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

**PLASTHERM®
PHF2E IRD**

*Halogen-free,
flame-retardant insulation
with reduced walls*

-40 °C to +105 °C



- 1 • Concentric tin-plated copper core.
- 2 • Halogen-free, flame-retardant thermoplastic insulation, reduced walls

Approvals - standards

- Resistance to vertical flame propagation for a single insulated wire. IEC 60332-1-2 / NF C 32-070 test C2
- Halogen-free, low corrosivity and acidity of gases evolved during combustion: EN 60754-1 and EN 60754-2
- Low smoke opacity: EN 61034-2

Applications

- Internal cabling for electrical and electronic appliances

**Characteristics
General**

- Continuous operating temperatures: -40 °C to +105 °C.
- Halogen-free, flame retardant, low toxicity, corrosivity and smoke opacity
- Good flexibility and mechanical strength, excellent resistance to abrasion.

Electrical

- Rated voltage: 250 V.
- Test voltage: 1 500 V.

Standard products

- All solid colours
- Surface marking (except AWG24)

PLASTHERM PHF2E IRD**Concentric tin-plated copper core**

Nominal cross-section (mm ²)	Equivalent cross-section AWG	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.22	24	7 x 0.20	92.5
0.34	22	7 x 0.25	59.2
0.6	20	19 x 0.20	33.7
0.93	18	19 x 0.25	21.6
1.34	16	19 x 0.30	15.0

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.25	1.10	2.9
0.25	1.30	4.4
0.40	1.75	7.6
0.40	2.00	11.1
0.45	2.35	15.9

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. (33) 04 73 82 50 00 - Fax (33) 04 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.
For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® PHFLEX

*Cable resistant to
alternate bending,
halogen-free insulation*
-35 °C to +90 °C



- 1 • Flexible tin-plated copper core – Class 6 as per IEC 60228.
- 2 • Halogen-free, flame-retardant thermoplastic insulation.
- 3 • Halogen-free, flame-retardant thermoplastic insulation.

Approvals - standards

As per EN 45545-2

- Resistance to vertical flame propagation for a single insulated wire as per EN 60332-1-2 report LAPI n° 1477.OCI0010/21.
- Low smoke opacity as per standard EN 61034-2 LAPI n° 1477.OCI0260/21.
- Tests on electric cables under fire conditions as per EN 50305 LAPI n° 1477.ICI0120/21.

Applications

- Cabling for electrical systems requiring high cable flexibility and specific conditions of use (fire, smoke, mechanical fatigue) for railway rolling stock.

Characteristics**General**

- Continuous operating temperatures: -35 °C to +90 °C.
- Halogen-free, flame retardant, low smoke toxicity and opacity
- Excellent flexibility and resistance to alternate bending, excellent resistance to abrasion.

Electrical

- Rated voltage: 450 / 750 V.
- Test voltage: 2 500 V.

Standard products

- Dual layer insulation.
- Solid inner layer, black outer layer or dual-colour yellow/green.

PLASTHERM PHFLEX**Extra-flexible core – class 6 as per IEC 60228**

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.5	105 x 0.08	40.1
0.75	152 x 0.08	26.7
1	210 x 0.08	20.0
1.5	192 x 0.10	13.7

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Minimum bending radius (mm)
0.6	2.20	10
0.6	2.50	20
0.7	2.70	40
0.8	3.30	50

For this product, please contact:

OMERIN division principale ✓

Zone Industrielle - F 63600 Ambert

Tel. (33) 04 73 82 50 00 - Fax (33) 04 73 82 50 10

omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force.

For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM®

Style 21209

Polyurethane sheathing

UL and cUL approval



- 1 • UL approved conductors.
- 2 • Outer sheath: Polyurethane

Characteristics

General

- Continuous operating temperatures: -20 °C to +90 °C.
- Excellent resistance to common chemical environments.
- Excellent mechanical strength and resistance to abrasion.

Electrical

- Rated voltage: 125 to 1 000 V according to style no. of single conductors used.
- Test voltage: 10 x Rated voltage.

Standard products

- Single conductors: UL and cUL approved PVC insulated conductors (≥ 90 °C -125 °C at 1 000 V).
- Standard outer sheath colour: black.
- Stranding of conducting cores: contact us.

Approvals - standards

- UL approval as per standard UL 758 - File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210 - File no.: E101965.
- "Cable flame test" as per UL approval.
- "FT1 flame rating" as per cUL approval.

Applications

- External or internal cabling for electrical appliances.

Options

- Other outer sheath colours: contact us.
- Other nominal cross-sections: contact us.

KEY

- conducting metals
- B** Tin-plated copper
- B*** Tin-plated copper (ø > 0.38 mm)
- C** Nickel-plated copper
- D** Silver-plated copper
- E** Nickel
- F** Bare copper
- F*** Bare copper (ø > 0.38 mm)
- G** Nickel-plated copper 27 %

AWM I A Internal wiring, not subject to mechanical abuse

AWM I A/B Internal wiring

AWM II A/B External or Internal wiring

NS Not Specified

VNS Voltage Not Specified

■ : UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation or the sheathing should be taken into account.

For this product, please contact:

OMERIN division principale ✓
Zone Industrielle - F 63600 Ambert
Tel. (33) 04 73 82 50 00 - Fax (33) 04 73 82 50 10
omerin@omerin.com



Style no.	21209-E90		21209-W12		21209-F90	
Approval	90 °C - 300 V		90 °C - 600 V		90 °C - 1,000 V	
Single conductor style no.	Style 10125		Style 10900		Style 10203	
	AWM I/II A/B		AWM I/II A/B		AWM I/II A/B	
No. of cond.	AWG	Nominal cross-section (mm²)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)	Nominal diameter* of the cond. (mm)	Nominal diameter* of the cable (mm)
2	26	0.13	0.75	3.1	1.2	4.0
3	26	0.13	0.75	3.2	1.2	4.1
4	26	0.13	0.75	3.4	1.2	4.5
5	26	0.13	0.75	3.6	1.2	4.8
7	26	0.13	0.75	3.8	1.2	5.2
2	24	0.22	0.9	3.4	1.4	4.4
3	24	0.22	0.9	3.5	1.4	4.6
4	24	0.22	0.9	3.7	1.4	4.9
5	24	0.22	0.9	4.0	1.4	5.4
7	24	0.22	0.9	4.3	1.4	5.8
2	22	0.34	1.05	3.7	1.5	4.6
3	22	0.34	1.05	3.8	1.5	4.8
4	22	0.34	1.05	4.1	1.5	5.2
5	22	0.34	1.05	4.4	1.5	5.6
7	22	0.34	1.05	4.7	1.5	6.1
2	-	0.5	1.25	4.1	1.7	5.0
3	-	0.5	1.25	4.2	1.7	5.2
4	-	0.5	1.25	4.6	1.7	5.7
5	-	0.5	1.25	4.9	1.7	6.2
7	-	0.5	1.25	5.3	1.7	6.7
2	20	0.6	1.3	4.2	1.75	5.1
3	20	0.6	1.3	4.4	1.75	5.3
4	20	0.6	1.3	4.7	1.75	5.8
5	20	0.6	1.3	5.1	1.75	6.3
7	20	0.6	1.3	5.5	1.75	6.8
2	-	0.75	1.4	4.4	2.0	5.6
3	-	0.75	1.4	4.6	2.0	5.9
4	-	0.75	1.4	4.9	2.0	6.4
5	-	0.75	1.4	5.4	2.0	7.0
7	-	0.75	1.4	5.8	2.0	7.6
2	18	0.93	1.55	4.7	2.1	5.8
3	18	0.93	1.55	4.9	2.1	6.1
4	18	0.93	1.55	5.3	2.1	6.6
5	18	0.93	1.55	5.8	2.1	7.3
7	18	0.93	1.55	6.2	2.1	7.9
2	-	1	1.65	4.9	2.9	7.4
3	-	1	1.65	5.1	2.9	7.8
4	-	1	1.65	5.5	2.9	8.6
5	-	1	1.65	6.0	2.9	9.4
7	-	1	1.65	6.5	2.9	10.3
2	16	1.34	1.9	5.4	3.0	7.6
3	16	1.34	1.9	5.6	3.0	8.0
4	16	1.34	1.9	6.1	3.0	8.8
5	16	1.34	1.9	6.7	3.0	9.7
7	16	1.34	1.9	7.3	3.0	10.6
2	-	1.5	2	5.6	3.1	7.8
3	-	1.5	2	5.9	3.1	8.2
4	-	1.5	2	6.4	3.1	9.0
5	-	1.5	2	7.0	3.1	10.0
7	-	1.5	2	7.6	3.1	10.9
2	14	-	2.25	6.1	3.4	8.4
3	14	-	2.25	6.4	3.4	8.9
4	14	-	2.25	7.0	3.4	9.8
5	14	-	2.25	7.7	3.4	10.8
7	14	-	2.25	8.3	3.4	11.8

Conducting metal

BCDF


BCDF

BCDF

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

**PLASTHERM®
MYBE-EY-CSI****-20 °C to +80 °C
INTRINSIC SAFETY**

- 1 • Flexible tin-plated copper core.
- 2 • Insulation: PVC 80 °C.
- 3 • Electrical shielding: tin-plated copper braid.
- 4 • Outer sheath: Special blue colour PVC

Applications

- Cable intended for instrumentation and control, for fixed intrinsic safety circuit installations.

Options

- Insulation and/or outer sheath made of PVC 105 °C: contact us.
- Other nominal cross-sections: contact us.
 - Other nominal stranding: contact us.
- Other numbers of conductors: contact us.

Characteristics**General**

- Continuous operating temperatures: -20 °C to +80 °C.
- Good resistance to thermal shock.
- Good mechanical strength.
- Good resistance to common chemical environments and hydrocarbons (except aromatic).

Electrical

- Rated voltage: 600/1 000 V.
- Test voltage: 3 000 V.

Other characteristics

- Flame retardant: Category C2 cables (NF C 32-070) and IEC 60 332-1
- Overlapping of electrical shield $\geq 60\%$

Standard products

- Standard conductor colours: black with white numbers.
- Standard outer sheath colour: blue.

Identification

Multi-conductor cables without an earth wire are identified as follows:

< Number of conductors > X < Cross-section > (mm²) (example: 3 X 0.75 mm²).

Multi-conductor cables with an earth wire are identified by the symbol G in the place of the X (example 3 G 0.75 mm²).

Flexible core • class 5 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
2 x 0.75	24 x 0.20	26.7
3 x 0.75	24 x 0.20	26.7
4 x 0.75	24 x 0.20	26.7
5 x 0.75	24 x 0.20	26.7
7 x 0.75	24 x 0.20	26.7
12 x 0.75	24 x 0.20	26.7
19 x 0.75	24 x 0.20	26.7
27 x 0.75	24 x 0.20	26.7
37 x 0.75	24 x 0.20	26.7
48 x 0.75	24 x 0.20	26.7
61 x 0.75	24 x 0.20	26.7

INSULATED CONDUCTORS

Nominal thickness of insulation (mm)	Nominal diameter (mm)
0.6	2.35
0.6	2.35
0.6	2.35
0.6	2.35
0.6	2.35
0.6	2.35
0.6	2.35
0.6	2.35
0.6	2.35
0.6	2.35
0.6	2.35

SHEATHED CABLE

Nominal diameter (mm)	Approximate linear weight (kg/km)
7.3	75
7.7	95
8.3	105
9.0	125
9.6	160
12.9	240
15.1	350
17.9	495
15.4	655
18.5	837
20.9	1053

For this product, please contact:

OMERIN division principale 
Zone Industrielle - F 63600 Ambert
Tel. (33) 04 73 82 50 00 - Fax (33) 04 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME


The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® HP-U

2-conductor flat cable

Thin insulation

-20 °C to +80 °C



- 1 • Solid bare copper core.
- 2 • Insulation: PVC.

Applications

- Internal cabling for electric, electronic, audio and video appliances.

Options

- Tin-plated copper core.
- Other nominal cross-sections: contact us.
- Identification using a coloured longitudinal stripe on one of the two conductors: contact us.

Characteristics

General

- Continuous operating temperatures: -20°C to +80°C.
- Compact design with thin insulation.
- Easy stripping and separating of conductors.

Electrical

- Rated voltage: 400 V.
- Test voltage: 4000 V.

Standard products


- All colours including two-coloured.

SOLID CORE

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20°C (Ω/km) (bare copper core)
2 x 0.20	1 x 0.50	93.1
2 x 0.28	1 x 0.60	64.7
2 x 0.38	1 x 0.70	36.0
2 x 1.00	1 x 1.13	18.1

INSULATED WIRE

Nominal outer Dimensions (mm)		Approximate linear weight (kg/km)
a	b	
1.2	2.7	0.6
1.4	3.0	0.85
1.75	4.0	1.2
2.4	5.1	2.8



For this product, please contact:

OMERIN division Berne
La Forie - F 63600 Ambert
Tel. (33) 04 73 82 03 81 - Fax (33) 04 73 82 18 69
berne@omerin.com

www.omerin.com




The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories. © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® HP-M

2-conductor flat cable

Thin insulation

-20 °C to +80 °C



- 1 • Flexible bare copper core.
- 2 • Insulation: PVC.

Applications

- Internal cabling for electric, electronic, audio and video appliances.

Options

- Tin-plated copper core.
- Other nominal cross-sections: contact us.
- Identification using a coloured longitudinal stripe on one of the two conductors: contact us.

Characteristics

General

- Continuous operating temperatures: -20°C to +80°C.
- Compact design with thin insulation.
- Easy stripping and separating of conductors.

Electrical

- Rated voltage: 400 V.
- Test voltage: 4000 V.

Standard products


- All colours including two-coloured.

FLEXIBLE CORE

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20°C (Ω/km) (bare copper core)
2 x 0.38	12 x 0.20	52.0
2 x 0.50	16 x 0.20	39.0
2 x 0.75	24 x 0.20	26.0
2 x 1	32 x 0.20	19.5
2 x 1.5	30 x 0.20	13.3
2 x 2.5	49 x 0.20	7.98

INSULATED CABLE

Nominal outer Dimensions (mm)		Approximate linear weight (kg/km)
a	b	
1.3	3.0	0.95
1.6	3.6	1.3
2.2	4.5	2.0
2.5	5.2	2.8
3.0	6.2	4.0
3.7	7.8	6.3



For this product, please contact:

OMERIN division Berne
La Forie - F 63600 Ambert
Tel. (33) 04 73 82 03 81 - Fax (33) 04 73 82 18 69
berne@omerin.com

www.omerin.com




The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories. © Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

PLASTHERM® HP-M-HT

2-conductor flat cable
Thin insulation

-20 °C to +105 °C



- 1 • Flexible bare copper core.
- 2 • Insulation: PVC 105°C.

Applications

- Internal cabling for electric, electronic, audio and video appliances.

Options

- Tin-plated copper core.
- Other nominal cross-sections: contact us.
- Identification using a coloured longitudinal stripe on one of the two conductors: contact us.

Characteristics

General

- Continuous operating temperatures: -20°C to +105°C.
- Compact design with thin insulation.
- Easy stripping and separating of conductors.

Electrical

- Rated voltage: 400 V.
- Test voltage: 4000 V.

Standard products


- All colours including two-coloured.

FLEXIBLE CORE

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20°C (Ω/km) (bare copper core)
2 x 0.38	12 x 0.20	52.0
2 x 0.50	16 x 0.20	39.0
2 x 0.75	24 x 0.20	26.0
2 x 1	32 x 0.20	19.5
2 x 1.5	30 x 0.20	13.3
2 x 2.5	49 x 0.20	7.98

INSULATED CABLE

Nominal outer Dimensions (mm)		Approximate linear weight (kg/km)
a	b	
1.3	3.0	0.95
1.6	3.6	1.3
2.2	4.5	2.0
2.5	5.2	2.8
3.0	6.2	4.0
3.7	7.8	6.3



For this product, please contact:



OMERIN division Berne
La Forie - F 63600 Ambert
Tel. (33) 04 73 82 03 81 - Fax (33) 04 73 82 18 69
berne@omerin.com

www.omerin.com



The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.

Notes





omerin
division principale

Headquarters and division principale
Zone industrielle - 63600 Ambert - France

Tel. +33 **(0)4 73 82 50 00**

Fax +33 (0)4 73 82 50 10

e-mail: omerin@omerin.com

omerin
division silisol

division silisol
B.P. 87 - 11, allée du Couchant Z.I. du Devey
42010 Saint-Etienne Cedex 2 - France

Tel. +33 **(0)4 77 81 36 00**

Fax +33 (0)4 77 81 37 00

e-mail: silisol@omerin.com

www.omerin.com